INFORMATION TO USERS

This manuscript has been reproduced from the microfilm master. UMI films the text directly from the original or copy submitted. Thus, some thesis and dissertation copies are in typewriter face, while others may be from any type of computer printer.

The quality of this reproduction is dependent upon the quality of the copy submitted. Broken or indistinct print, colored or poor quality illustrations and photographs, print bleedthrough, substandard margins, and improper alignment can adversely affect reproduction.

In the unlikely event that the author did not send UMI a complete manuscript and there are missing pages, these will be noted. Also, if unauthorized copyright material had to be removed, a note will indicate the deletion.

Oversize materials (e.g., maps, drawings, charts) are reproduced by sectioning the original, beginning at the upper left-hand corner and continuing from left to right in equal sections with small overlaps.

ProQuest Information and Learning
300 North Zeeb Road, Ann Arbor, MI 48106-1346 USA
800-521-0600

UMI[®]

THERMAL EXPANSION OF THE
NOBLE METALS BELOW 15°K .

by

Joseph F. Kos

Submitted in partial fulfillment
of the requirements for the degree of
Doctor of Philosophy

Department of Physics,
Faculty of Pure and Applied Science,
The University of Ottawa,
OTTAWA, Canada.

1967.

UMI Number: DC52366

INFORMATION TO USERS

The quality of this reproduction is dependent upon the quality of the copy submitted. Broken or indistinct print, colored or poor quality illustrations and photographs, print bleed-through, substandard margins, and improper alignment can adversely affect reproduction.

In the unlikely event that the author did not send a complete manuscript and there are missing pages, these will be noted. Also, if unauthorized copyright material had to be removed, a note will indicate the deletion.

UMI[®]

UMI Microform DC52366

Copyright 2007 by ProQuest LLC

All rights reserved. This microform edition is protected against unauthorized copying under Title 17, United States Code.

ProQuest LLC
789 East Eisenhower Parkway
P.O. Box 1346
Ann Arbor, MI 48106-1346

Approved for the Department of Physics

Supervisor

Chairman of the Examining Committee

Chairman of the Department

ABSTRACT

A dilatometer of exceptionally high sensitivity has been developed and used to measure the thermal expansion of polycrystalline samples of copper, silver and gold and of a single crystal of copper in the range 4.2 to 15°K. The results obtained for copper were in excellent agreement with the work of other researchers and the error estimates were sufficiently small to show that the theoretical calculations of Collins are not supported by measurements on a polycrystalline specimen of copper. Below 15°K the data points were well represented by the equation:

$$10^{10}\alpha = (1.54 \pm 0.04)T + (0.275 \pm 0.0027)T^3$$

The results obtained for a single crystal of copper were significantly different from those obtained for a polycrystalline sample yet they are also in disagreement with the theoretical value. Below 15°K the data fitted the equation:

$$10^{10}\alpha = (3.13 \pm 0.05)T + (0.255 \pm 0.003)T^3$$

Values of γ_0 (the low temperature limiting value of the Grüneisen parameter) for silver and gold were measured to be 2.04 ± 0.06 and 2.91 ± 0.02 respectively. The agreement with the theoretical values 2.22 and 2.92 is quite good. Below 6°K the thermal expansion of silver and gold was found to be anomalous as it was no longer proportional to the specific heat of these metals.

In order to obtain high accuracy in the values of thermal expansion it was necessary to measure temperature to about 0.01°K. For this purpose a method was developed to obtain an interpolation of the resistance versus temperature function in the range 4.2 to 10°K. This capability permitted a theoretical study of the

electrical resistivity of pure platinum which indicated that d-band electrons contribute significantly to the conductivity at low temperatures.

In the hope of obtaining better measurements of temperature indium resistance thermometers were designed and constructed. Their reproducibilities were measured and were found to exceed previously reported values for indium resistance thermometers.

DEDICATION

This work is dedicated to my parents a fraction of whose love and dedication is, it is hoped, reflected herein.

ACKNOWLEDGEMENTS

It is a pleasure to express my gratitude to Professor J. M. Robson whose consideration for and kindness to myself and to students in general is very much appreciated, and to Dr. G. Lamarche whose generous financial support of, and interest in this project made it possible, and to Dr. Y. P. Varshni with whom I have had the honour of many enlightening discussions, and from whom I have learned much. I am very much indebted to Lionel Savary and to Michel Drolet for their help with the experimental work and with the calculations, their dedication and friendship lightened a very heavy load. I should like to thank Miss Loretta Sawyer for her excellent typing of this thesis, the staff of the physics workshop for their help in constructing parts of the apparatus, and the many other people in this department and at N.R.C. whose suggestions, advice and material aid hastened this project to completion, and whose friendship shall not be forgotten. Most of all, I wish to thank my wife for the encouragement and understanding which carried both myself and this project over many an impass, and also for her help with calculations and with the preparation of this thesis.

The author also wishes to express his appreciation for a graduate fellowship provided by the Province of Ontario.

Statement of Originality

As far as the author is aware the following contributions are claimed to be original.

1. The design and construction of an L-C oscillator with a stability better than one part per million over a period of hours.
2. The application of the L-C oscillator in the development of a dilatometer whose sensitivity exceeds previously published values.
3. The use of the above to measure changes in the capacitance and inductance with very high precision.
4. The use of the dilatometer to measure the thermal expansion of polycrystalline copper, silver and gold and a single crystal of copper to high accuracy in the range 4.2 to 15°K, where measurements on gold and on single crystal of copper have not been available. The results of these measurements have led to unusually interesting discoveries particularly for the case of gold.
5. The design, construction and calibration of indium thermometers whose reproducibility was shown to be better than 0.01°K - better than previously reported.
6. Contributions to platinum thermometry which include:
 - (a) The establishment of a method of interpolating the resistance-versus-temperature function to an accuracy of

about 0.01°K in the 4.2 to 10°K range when calibration points above 10°K and below 4.2°K are available.

(b) An investigation into the resistivity of platinum which indicated that the accepted expressions for the ideal resistivity in the Sondheimer-Wilson correction term do not describe the experimental results satisfactorily.

(c) The development of a method of calculating the ratios of the ideal and residual resistivities of band 1 to that of band 2 and its application to several samples, the results of which suggest that d-band electrons contribute significantly to conduction - contrary to what was previously assumed.

TABLE OF CONTENTS

ABSTRACT	iii
DEDICATION	iv
ACKNOWLEDGEMENTS	v
STATEMENT OF ORIGINALITY	vi
TABLES OF CONTENTS	vii
LIST OF DIAGRAMS	viii
LIST OF TABLES	ix

Chapter I INTRODUCTION

1.1 THE THERMAL EXPANSION OF SOLIDS	1
1.2 A BRIEF OUTLINE OF LATTICE DYNAMICS	2
1.2 (a) The Classical Period	2
(b) The Modern Formulation of Lattice Dynamics	3
(c) Anharmonic Effects	5
1.3 ELECTRONS IN METALS	7

Chapter II EQUIPMENT AND EXPERIMENTAL TECHNIQUE

2.1 EQUIPMENT	11
2.2 THE CRYOSTAT	11
2.2 (a) The Dilatometer	11
(b) The Vacuum System	16
(c) The Dewars	18
2.3 TEMPERATURE MEASUREMENTS	18
2.4 EXPANSION MEASUREMENTS.	19
2.4 (a) Method	19
(b) Electronic Equipment.	23

Chapter III THERMOMETRY

3.1	INTRODUCTION	31
3.2	THE ELECTRICAL RESISTIVITY OF THERMOMETRICALLY PURE PLATINUM BELOW 11°K	32
3.3	HIGH PRECISION INDIUM RESISTANCE THERMOMETERS	49

Chapter IV DATA ANALYSIS

4.1	CURVE FITTING BY THE METHOD OF LEAST-MEAN-SQUARES	76
4.2	STABILITY OF THE OSCILLATOR CIRCUIT	78
4.3	TEMPERATURE DATA	80
4.4	EXPANSION DATA	82
4.5	ANALYSIS OF DATA	83

Chapter V RESULTS AND DISCUSSION

5.1	SPECIMENS	86
5.2	MEASUREMENTS ON POLYCRYSTALLINE COPPER BETWEEN 4.2 and 15°K.	86
5.2	(a) Purpose	87
	(b) Results for Polycrystalline Copper	88
	(c) Discussion	95
5.3	MEASUREMENTS ON A SINGLE CRYSTAL OF COPPER	95
5.3	(a) Purpose	95
	(b) Results for a Single Crystal of Copper	96
	(c) Discussion	101
5.4	MEASUREMENTS ON SILVER AND GOLD	105
5.4	(a) Purpose	105
	(b) Results	105
	(c) Discussion	113
5.5	CONCLUSION	115

LIST OF DIAGRAMS

Figure 1	The Dialatometer.....	12
Figure 2	Constant-Capacity Coaxial Cable.....	15
Figure 3	The Vacuum System and Dewar.....	17
Figure 4	Block Diagram of Electronics.....	22
Figure 5	Three-Terminal Capacitor and Its Equivalent Circuit.....	26
Figure 6	Modified Version of the Clapp Oscillator.....	26
Figure 7	The Variable-Frequency Oscillator.....	28
Figure 8	The Frequency Multiplier.....	29
Figure 9	Mixer, Amplifier, and Cathode Follower.....	30
Figure 10	Graph of α versus T for Silver Run 1.....	109
Figure 11	Graph of α versus T for Silver Run 2.....	110
Figure 12	Graph of α versus T for Gold.....	111
Figure 13	Graph of $\frac{C_L}{T^3}$ and $\frac{\alpha_L}{T^3}$ versus T for Silver and Gold.....	112

LIST OF TABLES

Table I (Paper 1)	Polynomial Curve Fit to Available Points for Thermometer 320.....	35
Table II (Paper 1)	Polynomial Curve Fit for Thermometer 320 (Points between 4.2° and 10° removed)...	36
Table III (Paper 1)	Polynomial Curve Fit to Available Points for Thermometer Pt. 1.....	36
Table IV (Paper 1)	Polynomial Curve Fit for Thermometer Pt. 1 (Points between 4.2° and 10° removed).....	37
Table V (Paper 1)	Polynomial Curve Fit to Available Points for Thermometer LN 1586296.....	37
Table VI (Paper 1)	Theoretical Curve Fit for Thermometers 320 and LN 1586296.....	40
Table VII (Paper 1)	Maximum Deviation of the Theoretical Values of W_T from the Experimental (Interpolated) Values of W_T Reduced to a Temperature Difference.....	41
Table VIII (Paper 1)	Best Theoretical Curve Fit for Thermometer 320.....	42
Table IX (Paper 1)	Values of α and β for Various Thermometers.....	43

Table I (paper 2)	Coefficients of Polynomial Fits to B3.....	71
Table II (Paper 2)	Reproducibility of Thermometer B3.....	72
Table I	A Comparison of Theoretical and Experimental Values of Grüneisen Gammas for Copper, Silver, and Gold.....	87
Table II	Experimental Results for Polycrystalline Copper - Run 1.....	89
Table III	Experimental Results for Polycrystalline Copper - Run 2.....	90
Table IV	Averages of the Values of a , b , α , α_A , and α_G given in Tables II and III.....	90
Table V	Calculation of γ and γ_L	93
Table VI	A Comparison of the Values of a , b , γ_0 , and γ_e Resulting from Recent Work by Several Investigators.....	94
Table VII	Results of Measurements on a Single Crystal of Copper - Run 1.....	97
Table VIII	Results of Measurements on a Single Crystal of Copper - Run 2.....	97
Table IX	Results of Measurements on a Single Crystal of Copper - Run 3.....	98
Table X	Results of Measurements on a Single Crystal of Copper - Run 4.....	98

Table XI	Averages of the Values of a , b , α , α_A , and α_G given in Tables VII to X.....	99
Table XII	Values of γ and γ_L calculated from Measurements of the Thermal expansion of a Single Crystal of Copper.....	100
Table XIII	Results of Measurements on Silver Runs 1 and 2.....	106
Table XIV	Calculations of γ and γ_L for Measurements on Polycrystalline Silver.....	107
Table XV	Results and Calculations of γ and γ_L for Polycrystalline Gold.....	108

Chapter I

INTRODUCTION

1.1 THE THERMAL EXPANSION OF SOLIDS

A study of the thermal expansion of materials reveals information concerning various interaction processes which occur in solids. The dilation is a direct result of the anharmonicity of the motion of the atoms, and in metals the electron gas also contributes to the change of dimensions with temperature. Although a considerable amount of work is being done to achieve an understanding of the processes which occur, very little progress has been made towards the development of a complete anharmonic theory of solids. A fair share of the responsibility for this lack of progress can be attributed to the paucity of accurate experimental data. Quite often a theory will contain more parameters than can be accounted for by the existing data. This is particularly true in the case of metals, where the validity of the adiabatic approximation is still in question, and dielectric data cannot be used to supplement other measurements. In addition, the effects of the valence electrons must be recognized and separated from those due to the lattice. On the other hand we may obtain information about the behaviour of electrons in metals by studying their effect on the thermal expansion. The present investigation is therefore a modest attempt to contribute some new and more accurate data to the now vast and intricate fields of lattice and electron dynamics.

1.2 A BRIEF OUTLINE OF LATTICE DYNAMICS

1.2 (a) The Classical Period

The subject of lattice dynamics was initiated in 1912 in a paper by Born and von Karman [1]. They assumed that harmonic restoring forces act on the atoms in equilibrium in a crystal. The differential equations which govern the motion of these atoms can then be obtained. By considering the propagation of plane waves of a given wavelength in an arbitrary direction it is possible to calculate the propagation velocity and the dispersion of these waves - and in the long wavelength limit to determine the constants of the crystal in terms of the restoring forces. The application of suitable boundary conditions determines the spectral distribution of the normal modes and permits the calculation of caloric quantities such as the specific heat. Born and von Karman however, were able to carry out the complete analysis only for a simple one-dimensional model.

In the same year Debye [2] presented his approximation to the frequency spectrum of a three-dimensional crystal. Though his approach was less fundamental, correlating thermal and elastic properties instead of calculating both in terms of the more elementary interatomic forces, it was a simple one-parameter model yielding theoretical values of specific heat which were in fair agreement with the experimental values for many substances. His theory enjoyed many years of popularity, however as more and better data became available it was necessary to revert to the more complicated but more

fundamental analysis instigated by Born and von Karman.

1.2 (b) The Modern Formulation of Lattice Dynamics

In modern work the motion of the nuclei and the electrons in crystal are described by the many-particle Schrodinger equation which, unfortunately is very complicated. The problem is simplified by assuming that the electrons follow smoothly the motion of the nuclei - this is the famous adiabatic approximation. It was given some justification by Born and Oppenheimer [3] who showed that the motions of the electrons could be accounted for by a suitable interaction potential between nuclei. This interaction potential can be expanded in successive powers of the displacement of nuclei from equilibrium as follows:

$$\Phi = \Phi_0 + \Phi_1 + \Phi_2 + \Phi_3 + \Phi_4 + \dots \quad (1.1)$$

where Φ_r is of the r^{th} order in the displacements.

An additional simplification is obtained by invoking the harmonic approximation - which was first introduced by Born and von Karman and in effect neglects all terms in (1.1) beyond Φ_2 .

The calculation of spectra on the Born-von Karman model (employing a simple cubic lattice and including only first and second order interactions) was pioneered by Blackman [4]. He chose a finite mesh of points to cover a significant region of q-space and grouped the normal frequencies for points of this mesh in a histogram to provide an approximation to the spectrum. His work showed that the true spectra were very different from the Debye approximation, but that the specific heat is rather

insensitive to the form of the spectrum. Many further refinements of this model improved the agreement with experiment for example: Smith [5]; Kellerman [6]; Houston [7]; Montroll [8]; Leighton [9]; von Hove [10]; Montroll [11]; Phillips [12]; Rosenstock [13]. It must be remembered however that experimental quantities such as the specific heat represent averages over spectra rather than the spectra themselves, and therefore do not provide a direct verification of the theoretical models.

Recent developments in experimental technique particularly in the field of neutron diffraction by single crystals (Brockhouse [14]) furnished direct measurements of the dispersion curves for longitudinal and transverse waves. The dispersion curves for directions of symmetry are simply connected to the force constants and are much more sensitive to changes in them than smoothed averages like the specific heat. The main conclusion which emerges from these results is that the theoretical models using only nearest- and second-neighbour interactions are inadequate. In some cases the inclusion of fourth or even fifth-neighbour interactions is insufficient to bring theory into correspondence with experiment. At this point the number of parameters becomes so large that it is difficult to know what physical significance can be attached to the estimates of the force constants. In consequence Cochran [15] has proposed a "shell model" in which the atom is replaced by a rigid ionic core surrounded by an electronic shell free to undergo displacement relative to the core. The adiabatic approximation is preserved by assuming that the

electron shells have zero mass. In this way only two physically meaningful parameters enter and fair agreement is obtained with the dispersion curves given by neutron diffraction.

With regard to metals, the theoretical position is less satisfactory, and the problem of taking into account the properties of conduction electrons has claimed a great deal of attention, however no completely adequate theory has emerged. An attempt to calculate the force constants of copper from first principles (White [16]) gives results in serious disagreement with the force constants obtained from standard lattice dynamics. Varshni and Shukla [17] have extended the calculations to include interactions out to any neighbour, but find that it gives poor results for the Debye temperature of copper.

1.2 (c) Anharmonic Effects

Under the harmonic approximation the equilibrium volume of a solid must remain a constant function of temperature thereby excluding calculations of thermal expansion, compressibility, or expansion due to zero-point energy. To take these properties into account requires the inclusion of higher order terms in the potential given by equation (1.1). The term Φ_3 represents the asymmetry of the mutual repulsion of the atoms and Φ_4 represents the general "softening" of the vibrations at large amplitude - both must be utilized to account for the thermal quantities. Detailed calculations to include these terms are, unfortunately, extremely formidable. A simplification is effected by reverting to the quasi-harmonic approximation which assumes that the vibrations remain harmonic in character but that the

vibrational frequency varies with changes in the volume of a solid. This ruse permits the derivation of Grüneisen's rule [18] which states that at low temperatures the coefficient of thermal expansion should be proportional to the specific heat at constant volume.

On the basis of the Debye model the equation of state of a solid can be expressed in the form

$$pV = - VE'_0(V) + \gamma_e E_T(V)$$

where E_0 and E_T are the non-thermal and thermal terms in the internal energy and

$$\gamma = - \frac{d(\ln \Theta)}{d(\ln V)}$$

where Θ is the Debye equivalent temperature and γ is dependent only on volume [19]. From thermodynamics it follows that

$$\frac{\alpha}{X} = \frac{\gamma C_V}{V} \quad (1.2)$$

where X is the compressibility and α is the coefficient of thermal expansion. (A complete derivation is given in Appendix II).

The relation (1.2) is essentially Grüneisen's rule and must be obeyed by any solid having a Debye frequency spectrum [19]. Although it has been verified experimentally over a large range of temperatures, as more accurate experimental data became available it was found to break down at temperatures below one quarter of the Debye equivalent temperature [20]. Since this discrepancy occurred at temperatures too high for the contribution of the electrons to be significant, it was concluded that the explanation was to be found in the vibrational

spectrum of the crystal. This investigation was carried out by Barron [21] in terms of the lattice dynamics of Born and von Karman. Essentially he did for γ what Blackman [4] did for α . Defining γ as a function of temperature he derived, in a general analysis applicable to all lattices the low and high temperature limits γ_0 and γ_∞ and also showed that the main variation between these limits occurs at temperatures of the order of 0.2α . His calculations for a cubic close-packed lattice with central forces between nearest neighbours gave a value $\gamma_\infty - \gamma_0 = 0.3$ and a behaviour of γ which was quantitatively similar to that found experimentally in monatomic metals.

The absolute value of γ depends on the force law assumed. For frozen noble gases Barron assumed a Mie-Lennard-Jones potential of the form

$$- \lambda r^{-6} + \mu r^{-12}$$

and found $\gamma_\infty = 3$ and $\gamma_\infty - \gamma_0 = 0.15$.

The effect of widening the potential well is to reduce the values of both γ and the difference $\gamma_\infty - \gamma_0$. Hence measurements of the thermal expansion of solids yield information concerning the form of interatomic forces in solids.

1.3 ELECTRONS IN METALS

The free-electron model of a metal had in the past, thrown a great deal of light on the properties of metals and was the basis of the whole theory. However modern experimental work concerning the ordinary transport properties such as electrical

and thermal conductivities, thermo-electric power, Hall coefficients, and magnetoresistance shows clearly that the free-electron model is quite inadequate. The coefficients are often of the wrong sign, show anomalies of functional behaviour with temperature and impurity content, do not satisfy conditions such as Matthiesen's rule, and are seldom in quantitative agreement with theory. These discrepancies led to a revisualization of the behaviour of the electrons in terms of zones and bands. The Fermi surface is no longer a simple sphere as for the case of a free-electron gas, but is distorted, in some cases, to monstrous forms - defying all attempts at a reasonably simple analysis.

The noble metals provide an opportunity of studying the effects of the distortion which in these cases is of manageable proportions. The shape of the Fermi surface was determined by a variety of methods: the anomalous skin effect (Pippard [22]), the de Haas - van Alphen effect (Schoenberg [23]), high field magnetoresistance (Alekseevski and Gaidvkov [24]), cyclotron resonance (Langenberg and Moore [25]), and ultrasonic attenuation (Gavenda and Morse [26]). All methods indicate that the Fermi surface is approximately spherical, bulging out to touch the Brillouin zone boundaries in the (1,1,1) directions with an appreciable area of contact. It is expected to deviate only slightly from a sphere in the (1,0,0) directions. This model provides better agreement with theory in most cases. However its application to the study of the thermal expansion of metals is only in the preliminary stages.

In measurements of the thermal expansion of metals at

low temperatures a contribution α_e which is linear in temperature has been found for a number of metals. This expansion can be interpreted (from a naive point of view) as the change in volume of the lattice required to maintain a constant electron "pressure" when the temperature changes. It is related to the electronic heat capacity at constant volume by a Gruneisen expression

$$\alpha_e = \gamma_e \frac{C_e X_T}{V}$$

where X_T is the isothermal compressibility, V the molar volume of the metal and γ_e the electronic Gruneisen parameter. The value of γ_e can be calculated theoretically from the logarithmic dependence on volume of the electronic density of states N at the Fermi surface. Varley [27] gives

$$\gamma_e = 1 + \left(\frac{d \ln N}{d \ln V} \right)_T$$

and shows that γ_e has the value $2/3$ for a free electron gas. Collins [28] has calculated its value for copper, silver and gold taking into account the distortion of the Fermi surface in the (1,1,1) direction. His calculations are based on the work of Templeton [29] who observed the de Haas - van Alphen effect in copper silver and gold under hydrostatic pressure and hence calculated the volume dependence of the area of cross-section of the necks where the Fermi surface meets the zone boundaries in the (1,1,1) directions. The values of γ_e calculated by Collins could be compared with experiment only for the case of copper since values for silver and gold were not available.

Unfortunately his value was considerably higher than the experimental result.

Chapter II

EQUIPMENT AND EXPERIMENTAL TECHNIQUE

2.1 EQUIPMENT

The apparatus used to measure the thermal expansion of metals was designed to fulfill three requirements. It was necessary to provide an environment in which the temperature of the sample could be varied from 4.2°K to 293°K . The temperature of the sample had to be measured to an accuracy of one-hundereth of a degree. Finally, changes in the length of the sample had to be measured to an accuracy of about 10^{-11} cm. per. cm. The techniques employed to meet these requirements are described in the following sections under the headings, The Cryostat, Temperature Measurements and Expansion Measurements.

2.2 THE CRYOSTAT

A cryostat was constructed to maintain the sample at any desired temperature to within several millidegrees between 4.2°K and 293°K . It consists of a dilatometer, a vacuum system, and a set of dewars.

2.2 (a) The Dilatometer

The dilatometer, Fig. 1, contains the sample to be measured. It is constructed entirely of copper and is enclosed in a copper can nine inches long and three inches in diameter, which provides a vacuum compartment. The sample S is soldered

FIG.1 THE DILATOMETER

to a base B which rests on three copper posts P_4 . Agate insulators 0.0300" thick and 1/8" by 3/16" are attached to the top surface of each support and the bottom of each foot of the base. A stainless steel ball bearing separates the agate insulators. The agate provides good electrical insulation and the stainless steel is a good thermal insulator. Agate has the property of being very hard, hence the area of contact between the ball bearing and the agate is extremely small and good thermal insulation is obtained. The base B is anchored to the cage by means of a clamp C which is similarly insulated from the base. The shape of the base is such that a change in its dimensions with temperature will not affect the position of the sample. This arrangement provides good electrical and thermal insulation as well as a rigid and stationary mount for the sample.

A copper cap is clamped to the top of the sample and acts as one plate of the capacitor. The second capacitor plate P_2 is bolted to the support S_2 which is electrically insulated from support S_1 and from the guard ring both of which are grounded. The guard ring is set flat with P_2 and surrounds it completely leaving a gap of about ten thousandths of an inch. Its function is to eliminate the "edge effects" of the capacitor plates.

Support S_3 is suspended from S_2 by three posts P_3 which are accurately machined to be of equal length. Three other posts P_4 are designed to be of proper length to accomodate the sample leaving a gap of about three thousandths of a centimeter. A final adjustment of the gap is made by means of the three adjusting screws, A. Samples of various lengths may be

measured by using different sets of posts P_4 .

A high-Q coil having an inductance of about $125\mu\text{h}$ is mounted below the vacuum chamber and is always immersed in liquid helium. A copper shield surrounding it ensures that the inductance is not altered by minute vibrations of the dewar - caused by the boiling of liquid nitrogen.

The electrical leads for the thermometer and heater enter the pumping line through stupakoff seals and are passed through it into the vacuum chamber. Feed-through seals are used throughout to minimize thermal emfs. The leads are thermally anchored by glypal cement to a post which screws into support S_1 and are finally soldered to a terminal strip which connects them with their proper components.

The leads from the capacitor and coil are passed through two co-axial cables to the variable frequency oscillator. These cables, Fig. 2, are specially designed to prevent changes in capacitance between the outer tube T and the lead L as the level of the helium drops with time. The lead L is made of stainless steel capillary tubing to ensure that the differential thermal expansion between it and the outer tube T is zero, thereby preventing mechanical strains on the vacuum seals.

The electrical shield S is a copper tube co-axial with L and thermally and electrically insulated from but mechanically fastened to T at its top end by a perspex bushing P. The bottom end is soldered to a copper sleeve which is always in contact with the helium bath; hence the entire tube S is always at 4.2°K and its dimensions remain unchanged as the helium level drops. The cables are sealed at both ends with stupakoff seals which

Fig:2 Constant Capacity Co-axial Cable

pass the electrical leads to the capacitor and coil. These leads are also passed through liquid helium in the chamber C to prevent a heat leak into the dilatometer via these leads.

The heater is made by winding some manganin wire on a copper rod which is cemented to a copper screw head with glyptal varnish. A piece of cigarette paper between the rod and the screw insures good electrical insulation. The platinum thermometer is placed in a copper holder which is similarly attached to another copper screw. Both are firmly screwed into the base B.

2.2 (b) The Vacuum System

The vacuum system is used to thermally isolate the sample from its surroundings and to decrease the temperature of the liquid helium to about 1.7°K by pumping on it. It consists of rotary pumps and a diffusion pump as well as a manostat, a manometer and a high vacuum ionization gauge as shown in Fig. 3.

The high speed rotary pump is used to pump over the helium bath decreasing the vapour pressure of the helium, thereby lowering its temperature. The vapour pressure and hence the temperature is measured by a mercury and oil manometer over the range 1.7°K to 4.2°K . A manostat controls the pressure over the helium very accurately premitting good temperature stability.

An oil diffusion pump backed off by a rotary pump is used to evacuate the dilatometer chamber and the co-axial cables to a vacuum of better than 10^{-5}mm. Hg. in about one hour. In order to cool the sample several millimeters of helium exchange

Fig : 3 The vacuum system and Dewar

gas are passed into the dilatometer establishing thermal contact between the sample and the liquid helium.

2.2 (c) The Dewars

Cooling of the dilatometer is accomplished by immersing it in liquid helium. For this purpose a set of two dewars are used - an outer nitrogen dewar and an inner helium dewar sufficiently large to accomodate a dilatometer $3\frac{3}{4}$ " in diameter. Its depth is $28\frac{1}{2}$ " permitting a running time (without retransfer) of about six hours. A hoist was built to facilitate elevating and lowering the dewars and it was placed on rails so that they could be easily rolled away from the apparatus.

2.3 TEMPERATURE MEASUREMENTS

The proper measurement of the temperature of the sample imposed several stringent requirements on the type of thermometer to be used. It was necessary to measure temperature to an accuracy of one hundereth of a degree from 4.2°K to 293°K . The thermal response had to be less than a fraction of a second. It was also preferable to use only one sensing device over the entire temperature range. Finally it was necessary to have a calibration accurate to one-hundereth of a degree over the entire range.

Several systems were considered and the final choice was a platinum resistance thermometer which fulfilled the above conditions from 11°K to 293°K . The task of extending its range

to 4.2°K proved to be quite involved and difficult. The procedure finally adopted is discussed in Chapter III.

The resistance of the platinum thermometer was measured with a Guildline Potentiometer (type 9174) using a galvanometer amplifier as a null detector. This equipment is capable of measuring to an accuracy of one hundredth of a microvolt. With a current of ten milliamperes it gives a resistance sensitivity of 10^{-6} ohms - sufficient to detect changes in temperature of several millidegrees. The potentiometric method eliminates the problems of the resistance and the changes in the resistance of the electrical leads. Reversing the current also permits the elimination of thermal potentials which normally become serious at a sensitivity of one-hundredth of a microvolt.

2.4 EXPANSION MEASUREMENTS

2.4 (a) Method

To obtain measurements of the change in length of a sample to an accuracy of 10^{-11} cm/cm a highly levered system must be employed. The method adopted consists of two "levers" used in series. The first "lever" makes use of the variation in the capacitance of two parallel plates with a change in the distance between them. As the sample changes in length it moves one plate of the capacitor with respect to another fixed plate. Typical values for the length of the sample and the gap between the plates are 10 cm and 2×10^{-3} cm respectively, hence a change in the length of the sample of 10^{-3} cm (i. e. a change of about

0.01%) produces a 50% change in the gap - the leverage ratio is therefore 2×10^{-4} .

The capacitance is related to the distance between the plates by

$$C = \frac{A}{4\pi\epsilon_0 D} \quad (2.1)$$

where A is the area of one of the plates.

Hence,

$$\delta C = - \frac{A}{4\pi\epsilon_0} \frac{\delta D}{D^2} \quad (2.2)$$

Dividing (2.2) by (2.1) gives

$$\frac{\delta C}{C} = - \frac{\delta D}{D} \quad (2.3)$$

The capacitor C is connected in series with a coil L to make an L-C circuit which determines the frequency of the variable frequency oscillator (V.F.O.). In this way minute changes in length are translated into frequency changes. The resonance frequency is given by

$$f = \frac{1}{2\pi} \sqrt{\frac{1}{LC}}$$

or $(2\pi)^2 f^2 LC = 1 \quad (2.4)$

Differentiating (2.4) yields

$$2f\delta f (2\pi)^2 LC + (2\pi)^2 f^2 L\delta C = 0$$

$$- \frac{\delta C}{C} = + \frac{2\delta f}{f} \quad (2.5)$$

From equations (2.3) and (2.5) we obtain

$$\delta D = 2 \frac{D}{f} \delta f \quad (2.6)$$

- indicating the relationship between changes in length and changes in frequency. In practice a correction must be applied to eq. (2.1) in order to account for the edge effects of a real capacitor; and in this case it amounts to about 1%. This modification must be passed along to eq. (2.6) which must also be altered to take into account the stray capacitances which are present in the actual circuit. A mathematical analysis of the circuit including these corrections is presented in Appendix I.

The frequency of the V.F.O. is compared with that of a standard frequency oscillator (S.F.O.) by mixing the two signals and determining the beat frequency with a frequency counter Fig.4. The beat frequency changes by exactly the same number of cycles as the frequency from the V.F.O. This arrangement acts as another lever - the ratio of the V.F.O. frequency to the beat frequency being equal to the leverage. A ratio of 10^4 is quite practical, where

$$\frac{\text{V.F.O. frequency}}{\text{beat frequency}} = \frac{4 \times 10^7 \text{ cycles}}{4 \times 10^3 \text{ cycles}} = 10^4$$

Though it is advantageous to use a low beat frequency and a high V.F.O. frequency practical considerations limit the range of both. The frequency of the L-C circuit is limited to 1 Mcs. by the effects of stray capacitances in the co-axial cables and in the dilatometer. On the other hand the beat frequency must be sufficiently large to accomodate relatively large changes in the length of the sample. In practice the range of variation is about 2 Kcs. to 20 Kcs.

To retain the benefits of a large leverage ratio and the

Fig. 4 BLOCK DIAGRAM OF ELECTRONICS

stability attainable at a reasonably low L-C frequency, the 1 Mcs. signal from the V.F.O. is frequency multiplied to 40 Mcs. The 5 Mcs. signal from the S.F.O. is also multiplied to 40 Mcs. and the two signals are mixed to give a beat frequency of about 10 Kcs.

The precision attainable by this arrangement can be calculated from eq. (2.6) and the fact that the change in the length of the sample is equal to the change in the spacing between the capacitor plates. Hence

$$\delta l = \delta D = \frac{2D}{f} \delta f \approx 5 \times 10^{-11}$$

where typical values are

$$\delta f = 1 \text{ cps.}$$

$$f = 40 \text{ Mcs.}$$

$$D = 10^{-3} \text{ cm.}$$

For a 10 cm. sample this corresponds to a theoretical detection limit of

$$\frac{\Delta l}{l} = (\Delta l) \text{ per cm.} = 5 \times 10^{-12} \text{ cm.per.cm.}$$

$$\approx \pm 50 \text{ fermies.}$$

2.4 (b) Electronic Equipment

The heart of the electronics is the series L-C circuit which selects the resonant frequency of the V.F.O. and determines its stability. The stability of the L-C circuit sets the actual limit to the maximum sensitivity attainable. Two factors govern the stability - the quality factor (Q) of the circuit and the effect of external influences on the circuit.

Theoretically the Q is given by the formula

$$Q = \frac{1}{R} \sqrt{\frac{L}{C}} \quad (2.7)$$

The values of L and C must be such that their physical size is convenient and that the proper resonance frequency is obtained. Typical values are $C \approx 200$ pf. and $L \approx 125$ μ h, hence $\sqrt{\frac{L}{C}} \approx 10^3$; while the value of R at helium temperatures is approximately 10^{-4} ohms, resulting in a calculated Q of about 10^7 . However in actual practice some energy is radiated by the coil to its surroundings. The loss in energy due to joule heating accounts for a D.C. resistance term - $R_{D.C.}$; whereas the loss in energy due to radiation can be simulated by introducing an additional resistance - ' $R_{\text{radiation}}$ '. Hence the proper value of R to be used in eq. (2.7) is given by

$$R = R_{D.C.} + R_{\text{radiation}}$$

- which yields a Q somewhat lower than the value calculated.

External influences on the L-C circuit belong to one of two categories. The first includes actual changes in the inductance and capacitance due to mechanical changes in these components brought about by vibrations or thermal variations. These have been minimized by designing extremely rigid mounts for the sample and for the inductance, by shielding the coil, by using a guard ring with the capacitor, and by submerging all critical components in liquid helium. On the other hand changes in stray capacitances and inductances throughout the dilatometer, the oscillator circuit and the connecting cables produce undesirable changes in frequency which may be represented by

"equivalent" changes in the L-C components. These are minimized by using components of high stability - zero temperature coefficient mica capacitors, air-dux coils, and specially designed co-axial cables; as well as a circuit designed such that fairly large changes in the stray capacitances and inductances are equivalent to only very small changes in L and C. A three-terminal capacitor arrangement (Fig. 5) eliminates what would otherwise be stray capacitances in parallel with the main capacitor C.

To complete the oscillator, an electron tube is used to provide the few db. of gain necessary to maintain oscillation, and a pi-network was chosen as a phase shifting device to provide the required 180° phase shift (in addition to the 180° shift produced by the electron tube.) Fig. 6. Two significant advantages are earned by using the pi-network as opposed to any other sort of phase shifting device. First it is possible to place all its components C_1 , C_2 and L_1 in liquid helium - insuring their stability against temperature effects. Secondly, C_1 and C_2 are large ($\approx .005 \mu f$) and very stable, and are employed in a manner such that they are in parallel with all the stray capacities (except C_g) - in effect swamping variation in these. Furthermore it is known that the chief contributions to instability in electron tube amplifiers are due to the variability of the effective grid input capacitances (i. e. the grid to cathode plus the grid to screen capacitances and the Miller effect capacitance). In the circuit used C_1 and C_2 are in parallel with the grid to cathode and the plate to cathode capacitances

Fig. 5 Three Terminal Capacitor & its Equivalent Circuit

Fig.6 Modified Version of the Clapp Oscillator

and being several thousand times as large effectively "swamp-out" variations of the tube capacitances. Variations of the Miller effect capacitance (i. e. the product of the grid to plate capacitance and the grid to plate voltage gain of the tube) are minimized by stabilizing the voltage gain by means of an automatic amplitude control circuit Fig. 7. This device also limits the power input into the resonant circuit to several milliwatts.

The automatic amplitude control depends on adequate control over the transconductance of the tube by grid bias variation. Voltages sufficient to exercise such control are obtained by two stages of amplification which also act as a buffer between the output and the oscillator. Finally a third stage of amplification provides a usable output. This combined unit is referred to as the V.F.O. and is a modified version of the high stability oscillator proposed by Clapp [30] and perfected by Felch and Isreal [31].

The S.F.O. is similar to the V.F.O. except that it is controlled by a 5 Mcs. crystal housed in a temperature stable oven. It is expected to provide a frequency stability of at least one part in 10^8 over a period of several days - far better than actually required. A frequency multiplier Fig. 8 and a mixer, beat frequency amplifier, and cathode follower Fig. 9 - all of standard design were built and used.

Fig. 7 The Variable Frequency Oscillator (V.F.O.)

CHAPTER III

THERMOMETRY

3.1 INTRODUCTION

The problem of measuring temperature accurately in the 4.2 to 11°K region is one of long standing and one on which a great deal of effort has been expended by individual researchers as well as by groups working at various national standards laboratories. The maximum accuracy which could be obtained with a platinum resistance thermometer was about 0.2°K in the 4.2 to 11°K region. This limit was essentially due to the fact that standards laboratories do not calibrate these thermometers below 11°K - a tradition initiated in the days when resistance measuring equipment was not sufficiently sensitive to provide good calibrations below 11°K (where the sensitivity of the platinum thermometer is low).

Modern potentiometric equipment however permits the use of platinum thermometers to measure temperature down to 2°K with an accuracy better than 0.01°K. We therefore endeavoured to derive an interpolation of the 4.2 to 11°K region in terms of theoretical equations. A verification of the theoretical method was attempted using a polynomial curve fit to the available calibration below 4.2°K and above 11°K. The two methods gave values in the "unknown region" which differed by as much as 0.03°K.

Subsequent investigation showed that the polynomial interpolation was accurate to better than 0.01°K but that the prevailing theoretical results were inadequate to give a good

interpolation in the required region. Appropriate modifications of the theory are proposed, and new concepts (concerning d-band conduction) are introduced in the following section.

In the early stages of our work on platinum thermometry it appeared that a substantial advance could not be made, therefore an alternate solution, that of constructing an indium resistance thermometer was also attempted. It had been reported by several investigators that the temperature sensitivity of an indium filament was about ten times that of platinum below 15°K , and that there was a possibility of representing the resistance versus temperature relation by a simple theoretical formula which could therefore provide the required calibration of the 4.2 to 11°K region. They however encountered problems in the construction of a practical indium thermometer. It was necessary to make a filament which has a sufficiently high room-temperature resistance to provide good sensitivity and at the same time to mount it in a strain-free, yet rugged manner to permit good reproducibility. We approached the problem of the design and construction of indium thermometers from a new point of view and perfected a thermometer which is reproducible to better than 0.01°K . A report of this project is presented in section three.

3.2 THE ELECTRICAL RESISTIVITY OF THERMOMETRICALLY PURE PLATINUM BELOW 11°K

This section consists of a paper reporting advances in the field of platinum resistance thermometry.

THE ELECTRICAL RESISTIVITY OF THERMOMETRICALLY PURE PLATINUM BELOW 11 °K

J. F. KOS AND J. L. G. LAMARCHE

Department of Physics, University of Ottawa, Ottawa 2, Canada

Received October 14, 1966

A method is developed to obtain an interpolation of the resistance versus temperature function of pure platinum to an accuracy of about 0.01 °K in the range 4.2 to 10 °K, when calibration points below 4.2 and above 10 °K are available for a given sample. A study is made of the application of the two-band model to platinum in the range 1.5 to 11 °K. It is found that the accepted expressions for the ideal resistivity and for the Sondheimer-Wilson correction term do not describe the experimental results satisfactorily. Calculations of the ratio of the residual resistivity of band 2 to that of band 1, and of the ratio of the ideal resistivity of band 2 to that of band 1 indicate that electrons in the second band contribute significantly to the conductivity of platinum. A new expression for the ideal resistivity is proposed to account for the conductivity of the second band.

1. INTRODUCTION

The variation of resistance with temperature of thermometrically pure platinum has been thoroughly studied in the range 10–900 °K because of its applications to thermometry. Platinum thermometers are commonly used as secondary standards and are for this reason calibrated above 10 °K by various standards laboratories. Between 1.5 and 4.2 °K it is possible to obtain an accurate calibration relative to the vapor pressure of helium. The range between 4.2 and 10 °K is more difficult to calibrate and very little data are available in this region. Such data exist for one specimen, referred to as Pt 1, to an accuracy of 0.03° and for another (No. 320) calibrated to an accuracy of 5 millidegrees. These data are used to develop a method of interpolating the 4.2 to 10 °K range for platinum thermometers already calibrated above 10 and below 4.2 °K.

In previous studies of the resistivity of platinum below 10 °K, de Haas and de Boer (1933), White and Woods (1957), Berry (1963), and van Dijk (1964) have not included the Sondheimer-Wilson correction term required by the two-band model, which has, however, been frequently applied above 10 °K, as for instance by Schultz (1957), Sharevskaya and Strelkov (1961), Klemens and Lowenthal (1961), Berry (1963), and Lovejoy (1963).

It has been adequately demonstrated by van Dijk (1964) that the reduced resistance $R_T/R_{273} = W_T$ has the form

$$(1) \quad W_T - W_0 = pT^2 + qT^5$$

below 4.2 °K, where W_0 is the value of W_T for $T = 0$ °K and p and q are constants for a given thermometer. However $pT^2 + qT^5$ cannot be taken as the reduced ideal resistance $(W_T)_i$, since the coefficients p and q vary from specimen to specimen. It was first suspected that this variation might be due to the presence of the correction term given by the two-band model:

$$(2) \quad \lambda_T W_0 = \frac{W_0(W_T)_i}{a(W_T)_i + (bW_0/G)},$$

which varies as the ideal resistance at temperatures where $(W_T)_i \ll W_0$ but differs from specimen to specimen since b has a different value for each thermometer. If this were the case, then the application of the correction in the range from 1.5 to 11 °K should yield some coefficient p_1 and q_1 of $(W_T)_i = p_1 T^2 + q_1 T^6$ applicable to all sufficiently pure samples of platinum. It will be shown that this approach is not satisfactory, since for most thermometers studied in this work the theoretical expression does not fit the calibration between 4.2 and 11 °K to better than 0.05 °K. The implications of the above equations are reexamined for this low-temperature range and evidence for the importance of conduction by a second band is presented. Assuming that each band has the form given by equation (1), the ideal resistance takes a new form and the theoretical expression for W_T is modified accordingly. In addition, the parameters a and b of the correction terms are shown to be temperature dependent, tending to constant values at very low and at high temperatures. The implications of this extension to the Sondheimer-Wilson theory are mentioned briefly, but a detailed test of it has to await more experimental data.

Section 2 describes a method for interpolating the W_T function in the range 4.2 to 10 °K. The significant equations for the low-temperature range are reviewed briefly in Section 3, and Section 4 is devoted to a test of these equations for a few thermometers. The ratios of the ideal and residual resistances of band 1 to those of band 2 are given for various thermometers in Section 5, and Section 6 contains an extension of the two-band model for the low-temperature range. A discussion of the thermometers studied appears in Appendix I.

2. INTERPOLATION FORMULA FOR THE 4.2 TO 10 °K REGION

Many laboratories possess platinum thermometers calibrated above 10 °K and are equipped to calibrate them in the liquid helium range. It is shown below that by fitting the available calibrated points below 4.2 and above 10 °K to a fifth degree polynomial in temperature by the method of least mean squares, the in-between range can be obtained to an accuracy of about 0.01 °K. A polynomial of the fifth degree was indicated by curve fitting a variety of thermometers and varying the degree of the polynomials from 1 to 10. In each case, a polynomial of higher degree did not improve the fit significantly. Since graphs of resistance against temperature always show a slight bend around 16 °K, only points below 16 °K were used to obtain the polynomial.

To verify the validity of the interpolation, it is necessary to have samples that are already calibrated between 4.2 and 10 °K to determine whether or not the interpolated values correspond to the actual values. Complete and accurate data for this verification are available for only two samples: thermometer 320 and Pt 1.

Thermometer 320

All the available points were used to evaluate the coefficients of a polynomial

$$(3) \quad W_T = A + BT + CT^2 + DT^3 + ET^4 + FT^5.$$

Table I contains the values of the coefficients for 320, the curve fitted values,

TABLE I

Polynomial curve fit to available points for thermometer 320
(Coefficients of polynomial: $A = +0.434\,504\,17 \times 10^{-3}$,
 $B = -0.715\,095\,08 \times 10^{-6}$, $C = +0.185\,523\,242 \times 10^{-8}$,
 $D = -0.178\,178\,05 \times 10^{-6}$, $E = +0.250\,273\,65 \times 10^{-7}$,
 $F = +0.167\,601\,53 \times 10^{-9}$)

Temperature (°K)	Reduced resistance (curve fitted)	Absolute deviation
0.000	$0.434\,50 \times 10^{-3}$	0.13×10^{-6}
1.000	$0.434\,58 \times 10^{-3}$	0.15×10^{-6}
1.500	$0.437\,12 \times 10^{-3}$	0.12×10^{-6}
2.000	$0.349\,46 \times 10^{-3}$	0.53×10^{-7}
2.785	$0.444\,56 \times 10^{-3}$	0.50×10^{-7}
3.000	$0.446\,28 \times 10^{-3}$	0.68×10^{-7}
3.933	$0.455\,65 \times 10^{-3}$	0.10×10^{-6}
4.210	$0.459\,11 \times 10^{-3}$	0.88×10^{-7}
5.019	$0.471\,46 \times 10^{-3}$	0.87×10^{-8}
6.014	$0.492\,50 \times 10^{-3}$	0.11×10^{-6}
7.125	$0.526\,57 \times 10^{-3}$	0.17×10^{-6}
8.101	$0.569\,18 \times 10^{-3}$	0.17×10^{-6}
9.051	$0.625\,80 \times 10^{-3}$	0.28×10^{-7}
10.00	$0.701\,71 \times 10^{-3}$	0.16×10^{-6}
10.50	$0.750\,55 \times 10^{-3}$	0.39×10^{-7}
11.00	$0.807\,03 \times 10^{-3}$	0.19×10^{-6}
11.50	$0.871\,70 \times 10^{-3}$	0.55×10^{-7}
12.00	$0.945\,43 \times 10^{-3}$	0.98×10^{-7}
12.50	$0.102\,91 \times 10^{-2}$	0.29×10^{-6}
13.00	$0.112\,38 \times 10^{-2}$	0.22×10^{-6}
13.50	$0.123\,04 \times 10^{-2}$	0.11×10^{-6}
14.00	$0.135\,02 \times 10^{-2}$	0.17×10^{-6}
14.50	$0.148\,41 \times 10^{-2}$	0.35×10^{-6}
15.00	$0.163\,34 \times 10^{-2}$	0.31×10^{-6}
15.50	$0.179\,94 \times 10^{-2}$	0.39×10^{-6}

NOTE: standard deviation = $0.206\,5 \times 10^{-6}$.

the difference between them and the experimental points, and the standard deviation. The corresponding temperature difference between the experimental and curve fitted values is always less than 0.01 °K.

Next, all the points between 4.2 and 10.0° were removed from the computer program and the remaining data were processed as before. The results of this operation are displayed in Table II. Using these new coefficients, the interpolation was tried between 4.2 and 10 °K and gave an agreement with the experimental points to better than 0.01 °K in all cases, thus indicating the reliability of the interpolation proposed.

Thermometer Pt 1

The same procedure applied to Pt 1 gave similar results, as can be seen from Tables III and IV.

It should be noted that for the above two cases the standard deviation is about 0.2×10^{-6} .

A similar procedure was also applied to thermometers for which no calibration is available between 4.2 and 10 °K. These are now discussed.

TABLE II

Polynomial curve fit to thermometer 320 (points between 4.2° and 10° removed) (Coefficients of polynomial:

$$\begin{aligned} A &= +0.434\,448\,29 \times 10^{-3}, & B &= -0.544\,540\,56 \times 10^{-6}, \\ C &= +0.177\,319\,25 \times 10^{-5}, & D &= -0.167\,244\,04 \times 10^{-6}, \\ E &= +0.244\,452\,26 \times 10^{-7}, & F &= +0.177\,962\,32 \times 10^{-9} \end{aligned}$$

Temperature (°K)	Reduced resistance (curve fitted)	Absolute deviation
0.000	$0.434\,44 \times 10^{-3}$	0.77×10^{-7}
1.000	$0.435\,53 \times 10^{-3}$	0.11×10^{-6}
1.500	$0.437\,18 \times 10^{-3}$	0.69×10^{-7}
2.000	$0.439\,51 \times 10^{-3}$	0.61×10^{-8}
2.785	$0.444\,57 \times 10^{-3}$	0.58×10^{-7}
3.000	$0.446\,28 \times 10^{-3}$	0.63×10^{-7}
3.933	$0.455\,57 \times 10^{-3}$	0.27×10^{-7}
4.210	$0.459\,01 \times 10^{-3}$	0.47×10^{-8}
10.00	$0.701\,60 \times 10^{-3}$	0.50×10^{-7}
10.50	$0.750\,46 \times 10^{-3}$	0.12×10^{-6}
11.00	$0.806\,97 \times 10^{-3}$	0.25×10^{-6}
11.50	$0.871\,67 \times 10^{-3}$	0.83×10^{-7}
12.00	$0.945\,43 \times 10^{-3}$	0.94×10^{-7}
12.50	$0.102\,91 \times 10^{-2}$	0.31×10^{-6}
13.00	$0.112\,38 \times 10^{-2}$	0.25×10^{-6}
13.50	$0.123\,05 \times 10^{-2}$	0.14×10^{-6}
14.00	$0.135\,02 \times 10^{-2}$	0.13×10^{-6}
14.50	$0.148\,41 \times 10^{-2}$	0.33×10^{-6}
15.00	$0.163\,34 \times 10^{-2}$	0.32×10^{-6}
15.50	$0.179\,94 \times 10^{-2}$	0.35×10^{-6}

NOTE: standard deviation = $0.220\,1 \times 10^{-6}$.

TABLE III

Polynomial curve fit to available points for thermometer Pt 1 (Coefficients of polynomial: $A = +0.351\,762\,14 \times 10^{-3}$, $B = +0.107\,784\,88 \times 10^{-4}$, $C = -0.258\,681\,71 \times 10^{-5}$, $D = +0.634\,990\,41 \times 10^{-6}$, $E = -0.356\,591\,44 \times 10^{-7}$, $F = +0.175\,677\,24 \times 10^{-8}$)

Temperature (°K)	Reduced resistance (curve fitted)	Absolute deviation
2.490	$0.371\,16 \times 10^{-3}$	0.77×10^{-7}
3.000	$0.375\,49 \times 10^{-3}$	0.45×10^{-7}
3.360	$0.379\,06 \times 10^{-3}$	0.42×10^{-7}
3.500	$0.380\,59 \times 10^{-3}$	0.33×10^{-7}
4.250	$0.390\,39 \times 10^{-3}$	0.32×10^{-8}
5.280	$0.409\,52 \times 10^{-3}$	0.43×10^{-7}
6.750	$0.452\,53 \times 10^{-3}$	0.84×10^{-7}
7.410	$0.479\,66 \times 10^{-3}$	0.17×10^{-6}
8.510	$0.538\,87 \times 10^{-3}$	0.40×10^{-7}
8.820	$0.559\,25 \times 10^{-3}$	0.90×10^{-9}
9.070	$0.577\,02 \times 10^{-3}$	0.21×10^{-7}
9.960	$0.651\,17 \times 10^{-3}$	0.33×10^{-6}
11.01	$0.764\,57 \times 10^{-3}$	0.47×10^{-6}
11.50	$0.829\,01 \times 10^{-3}$	0.28×10^{-6}
12.00	$0.903\,57 \times 10^{-3}$	0.32×10^{-6}
13.14	$0.111\,25 \times 10^{-2}$	0.39×10^{-6}
13.50	$0.119\,14 \times 10^{-2}$	0.13×10^{-6}
14.09	$0.133\,64 \times 10^{-2}$	0.35×10^{-6}
14.50	$0.144\,97 \times 10^{-2}$	0.44×10^{-6}
15.31	$0.170\,77 \times 10^{-2}$	0.28×10^{-6}

NOTE: standard deviation = $0.286\,6 \times 10^{-6}$.

TABLE IV

Polynomial curve fit to thermometer Pt 1 (points between 4.2° and 11 °K removed) (Coefficients of polynomial:
 $A = +0.351\,642\,10 \times 10^{-3}$, $B = +0.109\,821\,83 \times 10^{-4}$,
 $C = -0.266\,822\,47 \times 10^{-5}$, $D = +0.645\,956\,08 \times 10^{-6}$,
 $E = -0.362\,526\,89 \times 10^{-7}$, $F = +0.176\,784\,78 \times 10^{-8}$)

Temperature (°K)	Reduced resistance (curve fitted)	Absolute deviation
2.490	$0.371\,19 \times 10^{-3}$	0.47×10^{-7}
3.000	$0.375\,50 \times 10^{-3}$	0.54×10^{-7}
3.360	$0.379\,05 \times 10^{-3}$	0.32×10^{-7}
3.500	$0.380\,57 \times 10^{-3}$	0.15×10^{-7}
4.250	$0.390\,33 \times 10^{-3}$	0.64×10^{-7}
9.960	$0.651\,08 \times 10^{-3}$	0.24×10^{-6}
11.01	$0.764\,52 \times 10^{-3}$	0.42×10^{-6}
11.50	$0.828\,99 \times 10^{-3}$	0.30×10^{-6}
12.00	$0.903\,57 \times 10^{-3}$	0.32×10^{-6}
13.14	$0.111\,25 \times 10^{-2}$	0.37×10^{-6}
13.50	$0.119\,14 \times 10^{-2}$	0.11×10^{-6}
14.09	$0.133\,64 \times 10^{-2}$	0.37×10^{-6}
14.50	$0.144\,97 \times 10^{-2}$	0.45×10^{-6}
15.31	$0.170\,76 \times 10^{-2}$	0.30×10^{-6}

NOTE: standard deviation = $0.362\,0 \times 10^{-6}$.

Thermometer LN 1586296

This thermometer was calibrated at the laboratories of the National Research Council of Canada at 11, 12, and every two degrees thereafter to 40 °K. Points were then obtained in our laboratory at 4.21, 1.93, and 1.77 °K, relative to the 1958 helium vapor pressure scale. A check point was taken at 3.412 °K, relative to the superconducting transition in indium. W_0 was obtained by solving equation (1), using three calibrated points below 4.2 °K. These points, when plotted on a graph $(W_T - W_0)/T^2$ versus T^2 , fell on a straight line. Points at 2.5, 3.0, and 4.0° were obtained from the graph. All the available points between 0 and 16 °K were fitted, using the same computer program as above. The data for this thermometer and the curve fitted values are given in Table V.

TABLE V

Polynomial curve fit to available points for thermometer LN 1586296 (Coefficients of polynomial: $A = +385\,665\,18 \times 10^{-3}$, $B = -0.943\,754\,24 \times 10^{-6}$, $C = +0.222\,504\,83 \times 10^{-5}$, $D = -0.249\,470\,77 \times 10^{-6}$, $E = +0.321\,449\,95 \times 10^{-7}$, $F = -0.683\,797\,28 \times 10^{-10}$)

Temperature (°K)	Reduced resistance, W_0 (experimental)	Reduced resistance, W_0 (curve fitted)	Deviation $W_0 - W_0$
0.000	$0.385\,64 \times 10^{-3}$	$0.385\,66 \times 10^{-3}$	-0.25×10^{-7}
1.771	$0.390\,04 \times 10^{-3}$	$0.389\,90 \times 10^{-3}$	$+0.13 \times 10^{-6}$
1.968	$0.391\,06 \times 10^{-3}$	$0.391\,00 \times 10^{-3}$	$+0.55 \times 10^{-7}$
2.500	$0.394\,51 \times 10^{-3}$	$0.394\,56 \times 10^{-3}$	-0.53×10^{-7}
3.000	$0.398\,55 \times 10^{-3}$	$0.398\,71 \times 10^{-3}$	-0.16×10^{-6}
3.412	$0.402\,59 \times 10^{-3}$	$0.402\,76 \times 10^{-3}$	-0.17×10^{-6}
4.000	$0.409\,73 \times 10^{-3}$	$0.409\,68 \times 10^{-3}$	$+0.46 \times 10^{-7}$
4.210	$0.412\,71 \times 10^{-3}$	$0.412\,52 \times 10^{-3}$	$+0.18 \times 10^{-6}$
11.00	$0.772\,00 \times 10^{-3}$	$0.772\,09 \times 10^{-3}$	-0.91×10^{-7}
12.00	$0.913\,30 \times 10^{-3}$	$0.913\,20 \times 10^{-3}$	$+0.94 \times 10^{-7}$
14.00	$0.132\,22 \times 10^{-2}$	$0.132\,21 \times 10^{-2}$	-0.20×10^{-7}
16.00	$0.195\,33 \times 10^{-2}$	$0.195\,32 \times 10^{-2}$	$+0.17 \times 10^{-8}$

NOTE: standard deviation = $0.151\,2 \times 10^{-6}$.

Other Thermometers

Similar calculations were carried out for data given by van Dijk. The standard deviation is given in brackets for the various specimens: A2 (0.33×10^{-6}), 148 (0.24×10^{-6}), 120 (0.41×10^{-6}), 126 (0.12×10^{-6}), and LN 1137601 (0.16×10^{-6}). The standard deviations for these and for LN 1586296 compare favorably with those of thermometer 320 and Pt 1. In addition, the polynomial fitted the experimental points from 1.5 to 4.2 °K to about 0.02 °K and from 10 to 16 °K to about 0.01 °K. This evidence suggests that the interpolation procedure is as valid as in the case of 320 and Pt 1, even though no direct verification is possible.

3. THE TWO-BAND THEORY AT LOW TEMPERATURES

The two-band theory of metals proposed by Sondheimer and Wilson (1947) indicates that the resistivity ρ_T at any temperature T may be expressed as

$$(4) \quad \rho_T = (\rho_T)_i + \rho_r + \lambda_T \rho_r,$$

where the subscript i stands for the ideal part of the resistivity, i.e. that of a pure and physically perfect metal, and where ρ_r is the residual resistivity at 0 °K due only to impurities and physical imperfections of a real metal. The term $\lambda_T \rho_r$ represents the deviation from Matthiessen's rule when two-band conductivity is assumed.

In this theory it was assumed that Matthiessen's rule applies separately to each band and that the electrons in each band are independent of the others. Writing $\rho_1 = \rho_{i1} + \rho_{r1}$ for the first band, $\rho_2 = \rho_{i2} + \rho_{r2}$ for the second, $\rho_i = \rho_{i1} + \rho_{i2}$ for the total ideal resistivity, and $\rho_r = \rho_{r1} + \rho_{r2}$ for the total residual part, the deviation from Matthiessen's rule is

$$(5) \quad \lambda_T \rho_r = \rho_T - \rho_i - \rho_r = \frac{(\rho_{r2}\rho_{i1} - \rho_{r1}\rho_{i2})^2}{(\rho_{r1} + \rho_{r2})(\rho_{i1} + \rho_{i2})(\rho_{i1} + \rho_{r1} + \rho_{i2} + \rho_{r2})}.$$

Furthermore if the ratios of the ideal and the residual of resistivities of the two bands are defined as

$$(6) \quad \alpha = \rho_{i2}/\rho_{i1} \text{ and } \beta = \rho_{r2}/\rho_{r1},$$

equation (5) can be written as

$$(7) \quad \lambda_T \rho_r = \frac{\rho_i \rho_r}{a \rho_i + b \rho_r},$$

where

$$(8a) \quad a = \frac{(1 + \alpha)^2 \beta}{(\beta - \alpha)^2},$$

$$(8b) \quad b = \frac{(1 + \beta)^2 \alpha}{(\beta - \alpha)^2}.$$

Expression (7) is a convenient form of the correction term when the theory is compared with experiment.

It is now conventional to give equation (4) in terms of the reduced resistance $W_T = \rho_T/\rho_{273}$. This equation may be written as

$$(9) \quad W_T = W_0 + \lambda_T W_0 + (W_T)_i G,$$

where $G = [1 - W_0(1 + \lambda_{273})] = (\rho_{273})_i / \rho_{273}$ (Berry 1963).

Equation (7) may then be expressed as:

$$(10) \quad \lambda_T W_0 = \frac{(W_T)_i W_0}{a(W_T)_i + bW_0/G}.$$

For $T < 4.2^\circ\text{K}$, $(W_T)_i \ll W_0$ and

$$(11) \quad \lambda_T W_0 = (G/b)(W_T)_i,$$

i.e. the correction term is proportional to the ideal part. On the other hand, at high temperatures where $(W_T)_i \gg W_0$,

$$(12) \quad \lambda_T \simeq (1/a) \text{ high temperatures,}$$

which can be determined experimentally at high temperatures.

For comparison with experimental data, equation (9) can be written in full as

$$(13) \quad W_T = W_0 + \frac{(W_T)_i}{a(W_T)_i + bW_0/G} W_0 + [1 - W_0(1 + \lambda_{273})](W_T)_i.$$

For a given thermometer, a and b are calculated by solving equation (13) at 2 points (10 and 20°K), where W_T and $(W_T)_i$ are known, λ_{273} is calculated from data at 273°K and value of W_0 from data below 4.2°K . $(W_T)_i$ should be a universal function applicable to all pure samples of platinum.

On theoretical grounds, for sufficiently low temperatures previous authors have used the form

$$(14) \quad (W_T)_i = p_1 T^2 + q_1 T^5,$$

where the T^5 term is attributed to electron-phonon scattering (Bloch 1930) and the T^2 term to electron-electron scattering (Baber 1937). Using the approximation, equation (11), equation (13) becomes

$$(15) \quad W_T - W_0 = G(W_T)_i[1 + 1/b],$$

which is applicable below 4.2°K . Thus in this range the theory predicts that $W_T - W_0$ varies as $p_1 T^2 + q_1 T^5$, as found experimentally by van Dijk (1964).

4. TEST OF THE SONDHEIMER-WILSON THEORY IN THE 0 - 16°K RANGE

This test consists in comparing the W_T predicted by equation (13) and equation (14) with the experimental value of W_T available between 0 and 16°K . For thermometers 320 and Pt 1, experimental values are available over the whole range as mentioned in Section 2. For all other thermometers discussed, it was assumed that the interpolated values obtained by curve fitting were within 0.01°K of the true values.

To calculate W_T from equation (13), one must know a , b , W_0 , λ_{273} , and $(W_T)_i$. Assuming that the first four quantities are known for a given specimen, $(W_T)_i$ can be evaluated at a temperature T , where W_T is known by

solving equations (10) and (13). In this work, however, $(W_T)_1$ was found numerically from the two starting equations by an iteration process using an electronic computer. This method permitted a variation of the parameters a and b . The numerical value of $(W_T)_1$ was calculated at 4.21 and 11 °K, where W_T is known from experiment. Using these values, the constants p_1 and q_1 of equation (14) were calculated and equation (14) was used to obtain $(W_T)_1$ at any temperature in the range of interest. $(W_T)_1$ was finally reinserted in equation (13) to predict W_T and compare it with the experimental or curve fitted values. As an example, such a comparison is given in Table VI for thermometers 320 and LN 1586296. For these thermometers and all the

TABLE VI
Theoretical curve fit for thermometers 320 and LN 1586296

Temp. (°K)	$W(T)$ $\times 10^3$	$W_T(T)$ $\times 10^3$	$W_{II}(T)$ $\times 10^3$	TEFIT(T) $\times 10^3$	COR(T) $\times 10^6$	$W_I(T)$ $\times 10^3$	$W_{II}(T)$ $\times 10^3$
(a) Thermometer 320							
(Values of a and b used are $a = 4.40$, $b = 15.97$. Coefficients of T^2 and T^3 in equation (14) are $p_1 = 1.215 \times 10^{-6}$ and $q_1 = 1.290 \times 10^{-9}$).							
1.00	0.435 95	0.435 65	0.001 26	14.5	0.007 60	0.001 21	
2.00	0.439 55	0.439 53	0.005 07	0.38	0.030 58	0.004 89	
3.00	0.446 21	0.446 24	0.011 64	1.12	0.069 90	0.011 24	
4.00	0.456 36	0.456 36	0.021 42	0.26	0.128 26	0.020 75	
5.00	0.471 09	0.471 04	0.035 37	-1.34	0.210 76	0.034 39	
6.00	0.492 18	0.492 07	0.055 00	-3.34	0.325 48	0.053 75	
7.00	0.522 15	0.522 04	0.082 58	-5.09	0.483 48	0.081 18	
8.00	0.564 23	0.564 28	0.121 27	-5.98	0.698 22	0.119 99	
9.00	0.622 42	0.622 81	0.175 28	-5.56	0.983 97	0.174 53	
10.0	0.701 48	0.702 12	0.250 00	-3.59	1.353 1	0.250 43	
11.0	0.806 99	0.806 99	0.352 16	0.00	1.813 0	0.354 68	
12.0	0.945 33	0.942 38	0.489 99	5.23	2.361 9	0.495 83	
13.0	1.123 7	1.113 6	0.673 34	12.0	2.987 5	0.684 15	
14.0	1.350 2	1.326 9	0.913 86	20.5	3.667 0	0.931 74	
15.0	1.633 9	1.589 7	1.225 1	30.5	4.371 0	1.252 7	
16.0	1.984 5	1.911 5	1.622 7	42.0	5.068 3	1.663 3	
(b) Thermometer LN 1586296							
(Values of a and b used are $a = 4.26$, $b = 6.81$. Coefficients of T^2 and T^3 in equation (14) are $p_1 = 1.244 \times 10^{-6}$ and $q_1 = 1.260 \times 10^{-9}$).							
1.00	0.386 72	0.387 06	0.001 26	11.7	0.018 25	0.001 24	0.000 95
2.00	0.391 19	0.391 38	0.005 79	3.22	0.073 10	0.005 01	0.004 84
3.00	0.398 71	0.398 80	0.011 64	0.98	0.165 88	0.011 50	0.011 42
4.00	0.409 68	0.409 84	0.021 42	1.23	0.301 01	0.021 04	0.012 06
5.00	0.425 26	0.425 54	0.035 37	1.52	0.487 05	0.035 54	0.034 80
6.00	0.447 34	0.447 58	0.055 00	0.92	0.736 62	0.054 07	0.054 39
7.00	0.478 54	0.478 42	0.082 58	-0.34	1.064 7	0.082 72	0.082 28
8.00	0.522 21	0.521 39	0.121 27	-1.60	1.484 8	0.120 96	0.121 70
9.00	0.582 40	0.580 84	0.175 28	-2.22	2.003 8	0.175 25	0.176 68
10.0	0.663 87	0.662 20	0.250 00	-1.78	2.615 7	0.250 52	0.252 08
11.0	0.772 09	0.772 09	0.352 16	0.00	3.299 8	0.353 62	0.353 62
12.0	0.913 20	0.918 53	0.489 99	3.33	4.022 1	0.492 90	0.487 81
13.00	1.094 0	1.111 1	0.673 34	8.41	4.472 7	0.678 40	0.661 85
14.0	1.322 1	1.361 3	0.913 86	15.4	5.425 0	0.921 94	0.883 58
15.0	1.605 5	1.682 8	1.225 1	24.5	6.042 1	1.237 3	1.161 3
16.0	1.953 2	2.091 1	1.622 7	35.9	6.579 9	1.640 4	1.504 1

$W(T)$ = reduced resistance (curve fitted).
 $W_T(T)$ = reduced resistance (theoretical fit by equation (13)).
 $W_{II}(T)$ = reduced ideal resistance (Berry 1963).
 TEFIT(T) = temperature fit (temperature difference $W_T(T) - W(T)$).
 COR(T) = correction term ($\lambda T p_1$).
 $W_I(T)$ = ideal resistance (theoretical—from $(W_T)_1 = p_1 T^2 + q_1 T^3$).
 $W_{II}(T)$ = ideal resistance (calculated at each point separately—from $(W_T)_1 = (W_T - W_0 - \lambda_T W_0)/G$).

others under study, the maximum deviations between the theoretical and the experimental values are given in Table VII.

TABLE VII
Maximum deviation of the theoretical values of W_T from the experimental (interpolated) values of W_T reduced to a temperature difference

Thermometer	Maximum deviation (°K)
320	-0.06
Pt 1	-0.13
LN 1586296	+0.02
A2	+0.05
148	+0.05
147	+0.04
LN 1137601	+0.04
120	+0.04
126	+0.04

As can be seen from these tables, the agreement is not satisfactory and this suggests that either the theory was not properly applied or that the presently accepted formulation is a poor approximation.

To study the first alternative, let us examine in more detail how Table VI for resistor 320 was obtained. In this case the experimental values of W_T can be trusted within a few millidegrees. W_0 is obtained to the same accuracy, using the method of van Dijk (1964). The value of λ_{273} is adequately determined from high-temperature measurements. Furthermore, any error in this quantity would introduce a very small change in equation (13), since it appears only in a factor $(1 + \lambda_{273})$ multiplied by W_0 , which for pure metal is very small compared with unity. There remain three possibilities: the error is either in the parameters a and b or in the form of the expression adopted for $(W_T)_1$ (equation (14)), or in both.

Let us consider these possibilities in turn. The parameters a and b are derived from experimental data above 10 °K. It is not impossible that they are temperature dependent and have different values below 10 °K. To see if this could improve the agreement, a and b were assumed to be constant in the 4.2 to 11 °K range and hundreds of combinations of values of a and b (varying a from 0.1 to 8.0 and b from 0.1 to 21.0) were tried for 320. Noticeable improvements were obtained. As an example, Table VIII gives the results for the best agreement obtained when $a = 0.75$ and $b = 1.20$. However a and b are related to $(W_T)_1$ through equation (13) and $(W_T)_1$ was thereby inadvertently varied. The values of a and b which gave significantly better fits changed $(W_{11})_1$ from the value previously accepted by as much as 40%, being outside the established error limits by a factor of 10. The parameters were also varied for the eight other thermometers investigated and similar results were obtained. A change of this magnitude from the results quoted by other investigators was not justified. Hence this procedure did not lead to any conclusive results.

From

$$(W_T)_1 = [(W_T - W_0 - \lambda_T W_0)/G]$$

TABLE VIII

Best theoretical curve fit for thermometer 320 (Values of a and b used are $a = 0.75$, $b = 1.20$. Coefficients of T^2 and T^3 in equation (14) are $p_1 = 6.986 \times 10^{-6}$ and $q_1 = 8.979 \times 10^{-10}$. Symbols as in Table VI)

Temp. (°K)	$W(T)$ $\times 10^3$	$W_T(T)$ $\times 10^3$	$W_{III}(T)$ $\times 10^3$	TEFIT(T) $\times 10^2$	COR(T) $\times 10^5$	$W_I(T)$ $\times 10^3$	$W_{II}(T)$ $\times 10^3$
1.00	0.435 95	0.435 65	0.001 26	-15.0	0.058 23	0.000 69	0.000 86
2.00	0.439 55	0.439 53	0.005 07	-0.35	0.235 30	0.002 82	0.002 83
3.00	0.446 21	0.446 24	0.011 64	0.34	0.537 08	0.006 50	0.006 48
4.00	0.456 36	0.456 36	0.021 42	0.05	0.990 81	0.012 09	0.001 20
5.00	0.471 09	0.471 04	0.035 37	-0.26	1.641 3	0.020 27	0.002 02
6.00	0.492 18	0.492 07	0.055 00	-0.43	2.559 2	0.032 13	0.003 21
7.00	0.522 15	0.522 04	0.082 58	-0.31	3.337 7	0.049 32	0.004 93
8.00	0.564 23	0.564 26	0.121 27	0.10	5.582 2	0.074 13	0.007 41
9.00	0.622 42	0.622 81	0.175 28	0.57	7.889 6	0.109 60	0.010 93
10.0	0.701 48	0.702 12	0.250 00	0.70	10.818	0.159 65	0.015 92
11.0	0.806 99	0.806 99	0.352 16	0.00	14.360	0.229 14	0.022 91
12.0	0.945 33	0.942 38	0.489 99	-1.87	18.416	0.324 03	0.032 61
13.0	1.123 7	1.113 6	0.673 34	-5.01	22.806	0.451 45	0.045 91
14.0	1.350 2	1.326 9	0.913 86	-9.20	27.303	0.619 85	0.063 90
15.0	1.633 9	1.589 7	1.225 1	-14.0	31.677	0.839 05	0.087 69
16.0	1.984 5	1.911 5	1.622 7	-18.8	35.743	1.120 3	1.118 5

it is possible to calculate (by a process of iteration) values of $(W_T)_i$ at every degree, without assuming any particular form for $(W_T)_i$. This calculation was carried out for all thermometers and the average value of $(W_T)_i$ was obtained. The deviation of $(W_T)_i$ from the average is as high as four one-hundredths of a degree for some specimens, indicating that the values of a and b are to some extent responsible for the deviation of the experimental results from that predicted by theory.

The next point to consider is the form of equation (14) which was presumed to be valid to at least 11.0 °K, though it had been verified experimentally to only 4.2 °K. This form can be altered by an additional conduction due to a second band in platinum. Indeed, the very existence of the Sondheimer-Wilson correction term arises from the presence of such conduction. A calculation of the ratio of the resistivity of the second band to that of the first band would then indicate whether the form of equation (14) should be modified. This calculation is undertaken in the following section.

5. EVALUATION OF THE RESISTIVITY RATIOS α AND β

The values of α and β may be obtained from $S(a)$, (b) when the experimentally determined values of a and b are substituted into these equations. An explicit algebraic solution of α and β in terms of a and b is cumbersome, hence a method of successive approximation was adopted (Appendix II). The values of α and β for the thermometers studied are given in Table IX. In some instances two sets of values are given—corresponding to two sets of values of a and b , each set calculated at different temperatures. The reduced residual resistance W_0 is included as an indication of the purity of the various samples.

It will be noticed that the values of α and β are quite low, indicating that a significant proportion of the conduction is due to the second band. Lovejoy (1963) has determined the value of α to be 6 ± 1 for a group of thermometers.

TABLE IX

Values of α and β for various thermometers (α = ratio of ideal resistivity of band 2 to that of band 1 and β = ratio of residual resistivity of band 2 to that of band 1)

Thermometer	$W_0 \times 10^6$	a	b	α	β	a'	b'	α'	β'
Pt 1	362.1					1.77	5.44	2.9	14.2
Pt 2	484.0					0.62	7.12	6.0	92.7
320	433.0	4.11	11.34	5.2	18.4	4.40	15.97	8.8	37.8
120	689	3.33	10.97	5.8	24.3	3.84	8.65	3.3	10.7
126	943	1.78	6.87	4.1	22.8				
147	524					4.52	7.51	2.0	5.3
148	734					3.85	7.78	2.7	8.2
LN 1586296	385.6	4.02	9.10	3.5	11.2				
LN 113760	636					4.23	7.95	2.5	6.1

NOTE: a and b were determined from 20 and 90 °K points, whereas a' and b' were determined from 10 and 20 °K points.

We find, however, a wider range of variation for α , and also that α and β are very sensitive functions of a and b , whose values in turn depend on the temperatures at which they are calculated. Another interesting feature of these results is the change in the values of α and β from thermometer Pt 1 to Pt 2. These were made from the same material, but Pt 2 was subjected to a "small mechanical deformation". The introduction of physical defects appears to have increased the residual resistance of the second band by more than 700%, while the increase in the residual resistance of the first band was only about 25%. It is tempting to interpret the first band as the s band and the second band as the d band. If this is the case, then the observed behavior can be explained on the basis of a simple physical model. The effect of a physical deformation on the density-of-states function would indeed be predominant in the d band. This interpretation warrants serious consideration, since a knowledge of the resistivities of the s and d bands in transition metals would be quite useful in the study of the band structure of these metals.

6. APPLICATION OF THE TWO-BAND MODEL TO THE IDEAL RESISTIVITY

The form of the ideal resistivity at low temperatures (equation (14)) accounts for single-band conduction. However, in the preceding section it has been shown that a significant fraction of the conductivity of platinum may be attributed to the existence of a second band. In this case the above form must be applied to each band separately. Hence the ideal resistivity of band 1 may be written as

$$(16a) \quad (\rho_1)_1 = hT^2 + rT^5$$

and the ideal resistivity of band 2 as

$$(16b) \quad (\rho_1)_2 = gT^2 + sT^5,$$

where h , r , g , and s are "ideal" constants applicable to all sufficiently pure samples of platinum. The total ideal resistivity may now be written as

$$(17) \quad \rho_1 = \frac{(gT^2 + sT^5)(hT^2 + rT^5)}{(h + g)T^2 + (r + s)T^5}.$$

This expression reduces to the presently accepted form

$$(18) \quad \rho_1 = hT^2 + rT^5,$$

when the conductivity of the second band is neglected. In this case h corresponds to p_1 and r corresponds to q_1 . But $p_1 \gg q_1$, thus $h \gg r$, and presumably $g > s$ for the case where two-band conduction is assumed;* hence at low temperature, equation (17) reduces to

$$(19) \quad \rho_1 = \frac{gh}{h+g} T^2.$$

This form is in agreement with the results of de Haas and de Boer (1933) and van Dijk (1964) which established a T^2 variation of resistance with temperature below 4 °K.

It is now possible to write the exact expression for the ratio of the ideal resistivities as

$$(20) \quad \alpha_T = \frac{(\rho_1)_2}{(\rho_1)_1} = \frac{gT^2 + sT^5}{hT^2 + rT^5}.$$

This ratio is temperature dependent, but approaches the constant value g/h at very low temperatures and tends to another constant s/r at high temperatures. It should be noted that β is not a function of temperature but varies from thermometer to thermometer with the state of strain and the amount of impurities present. Since a and b are functions of α_T and β , they vary with temperature, as well as with the state of strain and the amount of impurities.

The ratio of the total resistivity of band 2 to that of band 1 is

$$(21) \quad \frac{\rho_2}{\rho_1} = \frac{(\rho_1)_2 + (\rho_r)_2}{(\rho_1)_1 + (\rho_r)_1}.$$

Invoking eq. (6) and the facts that

$$\frac{1}{\rho_1} = \frac{1}{(\rho_1)_2} + \frac{1}{(\rho_1)_1} = \frac{1}{(\rho_1)_1} \left[\frac{\alpha_T + 1}{\alpha_T} \right]$$

and

$$\frac{1}{\rho_r} = \frac{1}{(\rho_r)_2} + \frac{1}{(\rho_r)_1} = \frac{1}{(\rho_r)_1} \left[\frac{\beta + 1}{\beta} \right],$$

*Baber (1937) attributed the T^2 term to interband electron scattering. One can therefore argue that this term may be included only in the expression for the resistivity of band 1, as the scattering of "light" band-1 electrons by "heavy" band-2 electrons is considerable, while the reverse effect is believed to be small. If, however, the T^2 term is neglected, equation (16b) becomes

$$(\rho_1)_2 = sT^5 \quad (\text{case where } g \gtrsim s),$$

equation (16a) and the above now lead to

$$\rho_1 = \frac{sT^5(hT^2 + rT^5)}{hT^2 + (r+s)T^5},$$

which for $T < 4$ °K reduces to

$$\rho_1 = sT^5.$$

In view of the previously quoted experimental results, this must be rejected and a T^2 term must be included in the expression for the ideal resistivity of band 2.

eq. (21) becomes

$$(22) \quad \frac{\rho_2}{\rho_1} = \frac{(\alpha_T + 1)\rho_1 + (\beta + 1)\rho_r}{[(\alpha_T + 1)/\alpha_T]\rho_1 + [(\beta + 1)/\beta]\rho_r},$$

whose high and low temperature limits are α_T and β respectively.

The expression for the total resistivity as calculated from eqs. (4), (7), (8a), and (8b) is

$$(23) \quad \rho_T = \rho_r + \frac{\alpha_T}{\alpha_T + 1} (hT^2 + rT^5) + \frac{(\beta - \alpha_T)^2 (hT^2 + rT^5) \rho_r}{\beta(1 + \alpha_T)^2 (hT^2 + rT^5) + (\alpha_T + 1)(\beta + 1)^2 \rho_r}.$$

To facilitate comparison with experiment, eq. (23) may be put into the same form as eq. (13), namely

$$(24) \quad W_T = W_0 + G(W_T')_1 + \frac{W_0(\beta - \alpha_T)^2 G(W_T')_1}{\beta(1 + \alpha_T)^2 G(W_T')_1 + \alpha_T(1 + \beta)^2 W_0},$$

where G has the same definition as in eq. (9), but where

$$(25) \quad (W_T')_1 = \frac{\alpha_T}{\alpha_T + 1} \cdot \frac{(hT^2 + rT^5)}{(\rho_{273})_1}.$$

The low-temperature limit of this expression when $W_0 \gg hT^2 + rT^5$ and $hT^2 \gg rT^5$ is

$$(26) \quad W_T \approx W_0 + \frac{\alpha_T}{\alpha_T + 1} G \frac{hT^2}{(\rho_{273})_1} \left[1 + \frac{(\beta - \alpha_T)^2}{\alpha_T(1 + \beta)^2} \right],$$

corresponding to eq. (15), where

$$\left(\frac{\alpha_T}{1 + \alpha_T} \right) \cdot \frac{GhT^2}{(\rho_{273})_1}$$

is the reduced ideal resistivity and

$$\frac{(\beta - \alpha_T)^2}{\alpha_T(\beta + 1)^2} = \frac{1}{b}$$

is the Sondheimer-Wilson correction term. For highly strained specimens, $\beta \gg \alpha_T > 1$ and eq. (26) becomes

$$(27) \quad W_T - W_0 = \frac{\alpha_T}{1 + \alpha_T} \cdot G \frac{hT^2}{(\rho_{273})_1} \left[1 + \frac{1}{\alpha_T} \right] = \frac{hT^2}{\rho_{273}}.$$

It now becomes possible to evaluate h for specimens satisfying the above condition. Equation (20) relates g to h at low temperatures in the form $g = \alpha_T h$; hence g may also be found. If α_T is determined at two convenient temperatures, then eq. (20) yields two equations in two unknowns, r and s , whose values may then be obtained. An experimental verification of the proposed equations requires a series of experimental measurements of the resistance function of properly prepared samples of platinum representing a range of variation of impurities and strains.

CONCLUSION

In the temperature range considered, the experimental data do not support the theoretical expression (13) to better than 0.05 °K when the reduced "ideal" resistance is given by eq. (14) and constant values of a and b are used in eq. (7). A closer analysis of the nature of the correction term $\lambda_T \rho_i$ permits the calculation of the ratios of the residual and the ideal resistivities of the second band to those of the first band. The drastic increase of the residual resistance of the second band with a slight strain suggests that actual d -band electrons are involved. Calculations of these ratios indicate that electrons in the second band contribute significantly to the conductivity, justifying a two-band model, not only for the correction term but also for the "ideal" resistivity.

A theoretical approach based entirely on the two-band model reveals that the parameters a and b are temperature dependent, and gives the form of the ideal resistance. This expression reduces to the previously accepted form below 4.2 °K and at higher temperatures this approach yields a qualitative explanation of all the experimental results encountered. A quantitative verification requires measurements of properly prepared samples which will yield the "ideal" constants in eq. (17).

It has been demonstrated that for adequately calibrated thermometers a fifth-degree polynomial will fit the experimental calibration points below 16 °K to an accuracy of better than 0.01 °K. Where a calibration between 4.2 and 11 °K does not exist, the curve fit can be relied upon to interpolate this region with an accuracy of about 0.01 °K. Thus relatively inexpensive modern equipment* now permits the calibration and use of platinum thermometers to 2 °K with an accuracy of 0.01 °K. Since they are already used as international standards from 90 to 900 °K and are being seriously considered for this role between 12 and 90 °K, it is proposed that consideration be given to accepting the platinum resistance thermometer as the standard from 4.2 to 90 °K.

ACKNOWLEDGMENTS

The authors are indebted to Mr. Joseph Basinski of Northern Electric Company, R & D Laboratories, Ottawa, whose loan of thermometer LN 1586296 initiated this study. They are grateful to Mrs. D. Toop of the Computing Centre for her kind help with computer calculations. They owe to Mr. R. J. Berry of the National Research Council of Canada the calculation of the values of a and b , the graphical curve smoothing of the data for Pt 1, the permission to use data for 320, and the privilege of many discussions. This project has been supported by a grant-in-aid of research from the Department of University Affairs of the Province of Ontario, and one of us (J.F.K.) would like to acknowledge the aid of a Province of Ontario Fellowship.

APPENDIX I. EXPERIMENTAL DATA

Thermometer 320

This thermometer was calibrated by Martin and Berry of the National Research Council of Canada with respect to a gas thermometer constructed

*The Guildline potentiometer Type 9174 used with a photocell galvanometer amplifier type 9460 will measure to an accuracy of one hundredth of a microvolt.

by Martin (1966) and reported to be accurate to better than 5 millidegrees in the range 4.2 to 20 °K; it is also in agreement with the N.B.S. scale to within 0.01 °K in the 10 to 20 °K region. The experimental values of the reduced resistance are given by Berry (1967).

Pt 1 and Pt 2

The data for Pt 1 and Pt 2 were published by de Haas and de Boer (1933). The absence of points between 10 and 16 °K for Pt 2 precluded the use of our methods of calculation for this specimen. A curve fit through all the available calibration points below 16 °K for Pt 1 indicated a maximum scatter corresponding to ± 0.03 °K. Consequently the experimental points used here were the graphically smoothed ones (Berry 1967). Hence the standard deviation given in Table III is not an indication of experimental scatter.

Thermometers A2, 120, 126, 147, 148, and LN 1137601

Data below 4.2 °K may be obtained for these thermometers from van Dijk's publication (1964). Data above 10 °K were obtained from a personal communication via Mr. R. J. Berry. It was found that the curve fit to the available data was in all cases improved when the 10 °K point was excluded.

Thermometer LN 1586296

The data available on this thermometer are given in Section 2 of this paper.

APPENDIX II. CALCULATION OF α AND β

The values of α and β for a given thermometer may be found in terms of the experimental values a and b from eqs. (8a) and (8b). As the algebraic solution of these equations is tedious, an electronic computer has been employed to obtain α and β in the manner indicated below.

Equation (5) may be put into the form:

$$(28) \quad \lambda_T \rho_r = \frac{\rho_{r1} \rho_{11}}{\{[(1 + \beta)(1 + \alpha)^2]/(\beta - \alpha)^2\} \rho_{11} + \{[(1 + \beta)^2(1 + \alpha)]/(\beta - \alpha)^2\} \rho_{r1}}$$

$$(29) \quad = \frac{\rho_{r1} \rho_{11}}{A \rho_{11} + B \rho_{r1}},$$

which may be compared with

$$(7) \quad \lambda_T \rho_r = \frac{\rho_1 \rho_r}{a \rho_1 + b \rho_r}.$$

Both (29) and (7) are exact expressions for the correction term. Equation (7) is composed of experimentally determined terms ρ_1 , ρ_r , a and b , whereas eq. (29) relates α and β to A , B , ρ_{r1} and ρ_{11} , which cannot be measured directly.

We notice, however, that if the conductivity of the second band is very small, then $\rho_1 \simeq \rho_{11}$ and $\rho_r \simeq \rho_{r1}$ and in this case $a \simeq A$ and $b \simeq B$; thus to a good approximation

$$(30) \quad a \simeq A = \frac{(1 + \beta)(1 + \alpha)^2}{(\beta - \alpha)^2}$$

and

$$(31) \quad b \simeq B = \frac{(1 + \beta)^2(1 + \alpha)}{(\beta - \alpha)^2},$$

solving eqs. (30) and (31), yields an approximate value for α and β , namely

$$(32) \quad \alpha' = \frac{(B - A)^2}{B} - 1 \simeq \frac{(b - a)^2}{b} - 1$$

and

$$(33) \quad \beta' = \frac{(B - A)^2}{A} - 1 \simeq \frac{(b - a)^2}{a} - 1.$$

However $\rho_{12}/\rho_{11} = \alpha \approx \alpha'$ and $\rho_{r2}/\rho_{r1} = \beta \approx \beta'$; also

$$\frac{1}{\rho_r} = \frac{1}{\rho_{r2}} + \frac{1}{\rho_{r1}} \simeq \frac{1}{\beta' \rho_{r1}} + \frac{1}{\rho_{r1}};$$

therefore

$$(34) \quad \rho_{r1} \simeq \left(\frac{1 + \beta'}{\beta'} \right) \rho_r.$$

Similarly

$$(35) \quad \rho_{11} \simeq \left(\frac{1 + \alpha'}{\alpha'} \right) \rho_1.$$

Substituting eqs. (34) and (35) in eq. (29) gives

$$\lambda_T \rho_r \simeq \frac{\rho_1 \rho_r}{[\beta'/(1 + \beta')]A\rho_1 + [\alpha'/(1 + \alpha')]B\rho_r};$$

hence,

$$A \simeq \left(\frac{1 + \beta'}{\beta'} \right) a \text{ and } B \simeq \left(\frac{1 + \alpha'}{\alpha'} \right) b,$$

which is a better approximation than simply setting $A \simeq a$ and $B \simeq b$. Substituting A and B into eqs. (32) and (33) now gives more accurate values of α and β , which are now designated as α'' and β'' . The process is repeated until convergence occurs, yielding the required values of α and β . These may be substituted into (8a) and (8b) to verify the results of this method.

REFERENCES

- BABER, W. G. 1937. Proc. Roy. Soc. (London), Ser. A, 158, 383.
 BERRY, R. J. 1963. Can. J. Phys. 41, 946.
 ——— 1967. To be published.
 BLOCH, F. 1930. Z. Physik, 59, 208.
 DE HAAS, W. J. and DE BOER, J. 1933. Physica, 1, 609.
 LOVEJOY, D. R. 1963. C.I.P.M. Procès-verbaux des séances de 1962.
 KLEMENS, P. J. and LOWENTHAL, G. C. 1961. Australian J. Phys. 14, 352.
 MARTIN, D. L. 1966. Phys. Rev. 141, 576.
 SCHULTZ, H. 1957. Z. Angew. Phys. 9, 465.
 SHAREVSKAYA, D. I. and STRELKOV, P. G. 1961. Measurement Techniques (Oct.), p. 110
 (Translated from Izmeritel'naya Tekhnika, Feb. 1961, p. 16).
 SONDHEIMER, E. H. and WILSON, A. H. 1947. Proc. Roy. Soc. (London), Ser. A, 190, 499.
 VAN DIJK, H. 1964. Physica, 30, 1498.
 WHITE, G. K. and WOODS, S. B. 1957. Can. J. Phys. 35, 248.

3.3 HIGH PRECISION INDIUM RESISTANCE THERMOMETERS

This section contains a paper reporting advances in the field of indium resistance thermometry.

High Precision Indium Resistance Thermometers.

by

J. F. Kos, M. Drolet and J. L. G. Lamarche,
Department of Physics, University of Ottawa,
Ottawa 2, Ontario, Canada.

ABSTRACT

An account is given of the design, construction, calibration and reproducibility of two types of indium thermometers. The type B thermometer was found to be reproducible to better than 0.01°K between 4.2°K and room temperature. However thermometers employing indium from the same spool and constructed in the same way do not show the same Z-function; consequently each thermometer must be calibrated over the range in which it is to be used.

INTRODUCTION

The merits of employing an indium element in a resistance thermometer designed for use between 4.2°K and room temperature have been discussed by several authors. White and Woods (1957) pointed out the advantages of indium over other possible materials. The results of their measurements on several samples indicated that the reproducibility was affected by strains introduced in the indium filaments by the formers on which they were wound. In a following paper, White et al. (1958) reported that a filament wound on a mica cross and having a nominal room temperature resistance of four ohms proved to be reproducible "to about $\pm 0.01^{\circ}\text{K}$ at most temperatures". The effects of cycling on the ice point resistance were found to be small corresponding to changes of less than ± 3 m deg. Their values were tabulated in the form $Z = (R - R_{4.2}) / (R_{273} - R_{4.2})$ as a function of temperature. If Mathiessen's rule is valid, then all sufficiently pure specimens should have the same Z function and thermometers could be calibrated from the values given by these authors.

Yates and Panter (1961) and James and Yates (1963) proposed new designs which permitted the use of filaments of higher resistance. These thermometers were reproducible to several hundredths of a degree. Orlova et al. (1963)

introduced other designs for bifilar windings of very small diameter wire. They showed that although thermal cycling produces an increase in the resistance R_{273} , which is at first considerable, the effect decreases to a sufficiently stable values after five cycles. The phenomena is partly attributed to the diffusion of helium molecules into the indium at room temperature. They confirmed the suitability of the thermometers for the temperature range 3.4 - 300°K - but gave no indication of the reproducibility of their measurements.

These investigations established that good reproducibility could be obtained if the indium filament was supported in a strain free arrangement and that the R_{273} value could be stabilized by thermal cycling before calibration and subsequent use of the thermometer. Unfortunately the fragility and high ductility of thin indium filaments does not permit the construction of mica cross thermometers sufficiently rugged to withstand normal laboratory use. A second requirement for a practical thermometer is that the room temperature resistance be sufficiently high to permit accurate measurements of the resistance even when it has been decreased by a factor of

10^4 at 4.2°K . This condition is also difficult to achieve with a mica-cross thermometer of resonable proportions. We have therefore investigated two designs which appeared to fulfill the above mentioned requirements.

A series of careful measurements were taken to assess the reproducibility of these thermometers. The results were curve fitted by a method of least mean squares to provide a continuous function of resistance against temperature. In addition the effects of thermal cycling on the resistance-temperature curve (rather than just on the value R_{273}) were observed.

DESIGN AND CONSTRUCTION

Six thermometers were constructed using in all cases indium wire 99.999% pure and one hundredth of an inch in diameter. Three of these were of the design described as type A and the other three were labeled type B. The indium wire was supplied by the Indium Corporation of America⁽¹⁾ and came in lengths of several hundred feet wound on a spool.

Type A thermometers: These were made by winding a glyptal insulated length of indium wire on an indium rod. The wire, previously wound on a 5" diameter drum was slowly rewound on a second drum of the same diameter rotating in synchronism with the first. Between them the wire formed a large loop - dipping into a bowl of air drying glyptal varnish and drying out before being wound on the second drum. Only one coat of glyptal was applied to the wire used in thermometers A1 and A2 whereas three layers were applied to the wire used in thermometer A3. Several layers of this wire were wound on a rod of high purity indium. Such a unit was subsequently mounted in a copper capsule as shown in fig. I. A four terminal feed-through stupakoff seal was mounted on one end of the capsule. Each end of the indi

(1) The Indium Corporation of America, 1676 Lincoln Avenue, Utica 4, New York.

wire was soldered to a V-shaped copper wire whose ends were passed through and soldered to the terminals of the seal providing two current leads and two potential leads. Finally the capsule was evacuated, filled with one atmosphere of dry helium gas and sealed. The three thermometers of this type A1, A2, and A3 had room temperature resistances of approximately 12, 27 and 40 ohms respectively.

Type B thermometers: These were constructed using indium wire insulated with surgical grade teflon spaghetti having an outside diameter of 0.035" and an inside diameter of 0.015". Piano wire was pushed through a length of spaghetti and suspended vertically. The top end was soldered to the indium wire and the teflon spaghetti was clamped at this end. The piano wire was pulled from the bottom end, slowly drawing into the teflon tubing indium wire which was carefully unrolled off a spool. In this manner 35 foot lengths of the indium wire were easily insulated. The room temperature resistance of each length was about 18 ohms. After one layer of teflon covered indium wire was wound on a copper former, the teflon was cut away along the length of the former (except for B1)* exposing about one mm of indium wire from each loop. This procedure insured good thermal contact between

*In order to determine the effect of the teflon insulation on thermal response, the teflon cover was not cut in the case of thermometer B1.

the indium element and the exchange gas. A copper sleeve (about two thousandths of an inch thick) was slipped over the first layer and soldered to the base of the former providing a thermally anchored support for the second layer. In this way four successive layers were wound as shown in fig. 2. The capsules were now sealed following the same procedure as described for the type A thermometers. These three thermometers B1, B2 and B3 were "aged" for a period of about eight months. Thermometer B3 was then cycled between room temperature and the temperature of liquid nitrogen 24 times a day for several days, being immersed in liquid nitrogen for about 15 minutes, then removed for about 45 minutes by a motor driven mechanical device.

CALIBRATION AND REPRODUCIBILITY MEASUREMENTS

All calibrations were done with respect to a platinum thermometer (LN 1586296) which was calibrated above 11°K at the laboratories of the National Research Council of Canada to better than 0.01°K . Below 4.2°K it was calibrated in our laboratory with respect to the 1958 helium vapour pressure scale. The resistance-temperature relation between 4.2 and 11°K was obtained by a method of interpolation, discussed by Kos and Lamarche (1967), and is believed to be accurate to about $\pm 0.01^{\circ}\text{K}$. A Guildline type 9174 potentiometer and a type 9460 photocell galvanometer amplifier were used to measure the values of resistance to an accuracy of about $\pm 10^{-6}$ ohms for the type B design. However the galvanometer-amplifier detector was not available during calibration of the type A design and a simple galvanometer and scale (at a distance of about .45 feet) were used. The expected accuracy was about $\pm 3 \times 10^{-6}$ ohms corresponding to a maximum error of about $\pm .03^{\circ}\text{K}$ in temperature below 20°K .

Two sets of measurements were taken, the first set for A1, A2 and A3 thermometers, the second set for B1, B2 and B3 thermometers. Three indium thermometers and the platinum standard were coated with vacuum grease and inserted into wells drilled in a copper block $1\frac{1}{2}$ " in diameter and 4" long. The block was

coated with vacuum grease and fitted into a copper chamber. A heater of manganin wire was previously wound on and cemented to this chamber. The thermometer leads were passed from the chamber through a ten terminal feed-through stupakoff seal and were wound around and cemented to the chamber to minimize heat leaks into the thermometer filaments via the leads. The chamber was then vacuum sealed with an indium-o-ring, evacuated, filled with one atmosphere of helium gas and mounted in a cryostat as shown in fig. 3.

The temperature of the chamber was easily controlled to within a few millidegrees by manually varying the current through the heater.

Measurements on type A thermometers:

For A1 a total of eighty calibration points were taken in three separate runs covering a range from 4.2 to 80°K. The data obtained for A2 indicated that short circuits occurred intermittently between adjacent loops in the coil during the measurements. Eventually a short between two layers occurred at about 120°K changing the resistance by about 15%. A3 was calibrated between 4.2°K and room temperature and this calibration was followed up by two more reproducibility runs - yielding a total of 140 points.

Measurements on type B thermometers:

These measurements were carefully designed to facilitate an accurate least squares fit of the data. Points were taken at intervals of 0.2°K from 4.2 to 12°K ; of 0.5°K from 12 to 15°K ; of 1.0°K from 15 to 20°K ; of 2.5°K from 20 to 80°K ; of 5°K from 80 to 300°K , yielding a total of 140 points for each thermometer. These thermometers were then cycled between room temperature and nitrogen temperature four times and between room temperature and liquid helium temperature an additional six times over a period of about two weeks. A reproducibility run was then carried out.

ANALYSIS OF RESULTS

The data obtained from the calibration runs were curve fitted by the method of least mean squares to polynomials of the form $R = \sum_{i=0}^n A_i T^i$. To obtain good fits it was necessary to divide the 4.2 to 290°K region into seven parts and to represent each by a different polynomial. For example, table I gives the coefficients of the polynomials fitted to B3 and the range of the applicability of each polynomial. The degree of each polynomial as well as the most appropriate range were found by trial and error.

To determine the reproducibility, experimental points from the reproducibility run for each thermometer were compared with the values given by the polynomial expressions obtained from the previous run. The difference between the two sets of values is an indication of the reproducibility of a given thermometer.

Type A thermometers:

For A1, calibration data was obtained between 4.2 and 80°K and was curve fitted to four polynomials with an accuracy of about $\pm 0.02^\circ\text{K}$. As previously noted, the measurements for A2 were unreliable. The data for A3 was fitted to about $\pm 0.02^\circ\text{K}$ between 4.3 and 50°K and to better than $\pm 0.03^\circ\text{K}$ between 3.7

and 290°K . The reproducibility runs for A1 and A3 yielded results which were within $\pm 0.03^{\circ}\text{K}$ of the values obtained in the initial runs.

The method used for insulating the filaments of the type A thermometers does not produce dependable results as indicated by the breakdown of A2. However A3, which was covered with three layers of glyptal, has been handled over a period of two years during which no shorts had been detected. The differential thermal expansion between the glyptal and the indium probably introduces strains in the indium and gives rise to a poorer reproducibility. Yet, if a tolerance of two or three hundredths of a degree is permissible, a small, compact thermometer, or one of very high initial resistance, may be constructed.

Type B thermometers:

These thermometers were calibrated to better than 0.01°K and the polynomial curve fits passed through the experimental points with an average deviation of about 5 millidegrees. When the experimental points from the reproducibility runs were compared with the values given by the appropriate polynomials, they were found to agree to better than 0.01°K , for most points, for thermometers B2 and B3. The results

for B3 are given in table II which indicates that the reproducibility at most temperatures is several millidegrees. Four bad points occur around 90°K and may be attributed to a lack of good thermal equilibrium.

As previously noted, the teflon insulation was not cut for B1, hence the thermal contact was expected to be poor. To obtain an indication of the temperature lag for this design, readings were taken just after B3, B2 and the platinum thermometer reached equilibrium. It was found that B3 and B2 reach equilibrium in about the same time or sooner than the platinum thermometer, however it took about twice as long for B1. The lag was more pronounced at higher temperatures and resulted in a maximum error of 0.04°K above 190°K , whereas the error between 40 and 190°K was only 0.02°K and that between 4.2 and 40°K was less than 0.01°K . We may conclude that unless the teflon cover is opened to allow a direct contact of indium with the helium exchange gas, one must be prepared to wait somewhat longer to attain thermal equilibrium.

CONCLUSION

The reproducibility of the type B indium thermometer over the entire 4.2 to 290°K range was found to be about $\pm 0.01^{\circ}\text{K}$, which is better than previously reported for other designs. Since the measurement of reproducibility was probably limited by the accuracy of our measurements, rather than by the actual reproducibility of the resistance values, further studies (employing a better quality potentiometer and a primary thermometer of high reliability) would probably yield better values than quoted here.

Unfortunately the resistance function differs from one thermometer to another by a considerable amount though the thermometers were constructed of indium wire from the same spool. The smallest deviation (between B2 and B3) expressed in terms of temperature was as high as 0.1°K . This confirms the conclusion of Orlova et al. (1963) that the Z-function proposed by White and Woods (1957) is not sufficiently accurate for thermometric purposes. As a consequence each thermometer has to be calibrated at a number of points. This, however, is also the case for platinum thermometers.

Throughout the entire range the thermal response of B2 and B3 is as good as, or better, than that of the platinum thermometer - but B1 is inferior in this respect.

The type B design compares favourably with platinum thermometers as concerns ruggedness of construction. Moreover indium thermometers have an advantage over the latter in the 4.2 to 15°K region where their inherent temperature sensitivity is about ten times that of platinum thermometers. If the larger mass and hence the larger heat capacity of these thermometers is of no consequence, they may with advantage replace platinum thermometers particularly in applications where the equipment available for resistance measurements is not of the highest quality. Indeed, in these applications, the very magnitude of the heat capacity permits the employment of much higher measuring currents, swamping the effects of thermal e.m.f.'s, and providing high sensitivity.

ACKNOWLEDGEMENTS

The authors are pleased to express their gratitude to Dr. C. B. Benson who suggested the study of the resistivity of Indium, to Mr. Joseph Basinski of Northern Electric Company, R and D Laboratories, Ottawa, for the loan of the platinum thermometer, and to Mrs. D. Toop, Mr. Robert F. Whiting and Mr. Lionel Savary who helped with the calculations. This project has been supported by a grant-in-aid of research from the Department of University Affairs of the Province of Ontario.

FIG. 1

FIG. 2

FIG. 3

FIGURE CAPTIONS

Figure 1 Type A Indium Resistance Thermometer.

Figure 2 Type B Indium Resistance Thermometer.

Figure 3 Schematic Diagram of the Cryostat used in the calibration of thermometers. A - Line for pumping and for the electrical leads; B - Thermal anchor for the electrical leads; C - woods metal seal; D - ten terminal Stupakoff seal; E - indium "O"-ring seal; F - helium exchange gas; G - thermometer leads thermal anchoring; H - exchange gas or vacuum; I - copper block containing the thermometers; J - one of the three structural posts holding the base assembly; K - copper chamber for the block I; L - heater windings; M - Outer copper vacuum chamber; N - thermal insulation consisting of a stainless steel ball bearing between two thin slices of agate. There are three such supports. At the center a similar arrangement holds the thermally isolated part firmly in place.

TABLE I

Coefficients of Polynomial Fits to B3

Temperature Range in deg. K	Coefficients					
	$A_0 \times 10$	$A_1 \times 10$	$A_2 \times 10^4$	$A_3 \times 10^6$	$A_4 \times 10^7$	$A_5 \times 10^8$
4.200 to 8.379	-0.30965868	+2.2031785	-51.637333	+519.14462	-146.51399	
8.379 to 17.160	+0.90847677	-2.7538375	+25.207304	-21.766816		
17.160 to 41.880	+3.6349013	-8.3613779	+69.061414	-179.87007	+25.288211	-1.4900336
41.880 to 83.600	-5.3466200	+3.1833092	+7.3975316	-7.7089118	+0.30011848	
83.600 to 145.900	-10.716581	+6.5480378	-0.39466911	+0.22557409		
145.900 to 199.650	-3.8089032	+5.1358625	+0.57778732			
199.650 to 291.000	-1.9960068	+4.9485349	+0.62615188			

TABLE II

Reproducibility of Thermometer B3

Temperature (Second Run) (°K)	Resistance (From Curve Fits to First Run) (ohms)	Resistance (Second Run) (ohms)	Difference in Resistance	Difference in Temperature (°K)
4.802	0.0054531	0.0054765	+0.0000235	-0.012
5.250	0.0063679	0.0063468	+0.0000211	+0.009
5.636	0.0073399	0.0073313	+0.0000086	+0.003
6.306	0.0096392	0.0096359	+0.0000032	+0.000
7.227	0.014547	0.014555	+0.000008	-0.001
8.142	0.021924	0.021873	+0.000051	+0.005
8.229	0.022768	0.022748	+0.000020	+0.002
10.114	0.047658	0.047701	+0.000044	+0.003
12.107	0.088309	0.088245	+0.000064	+0.003
14.270	0.14793	0.14795	-0.00003	-0.001
16.109	0.21040	0.21042	-0.00002	-0.001
18.616	0.31028	0.31039	-0.00010	-0.002
20.202	0.38094	0.38084	+0.00010	+0.002
25.506	0.64850	0.64838	+0.00012	+0.002
31.473	0.98637	0.98634	+0.00003	+0.000
35.391	1.2211	1.2212	-0.0001	-0.002
40.168	1.5155	1.5155	+0.0000	+0.000
47.101	1.9480	1.9480	+0.0000	+0.000

Table II (cont'd)

Temperature (Second Run) (°K)	Resistance (From Curve Fits to First Run) (ohms)	Resistance (Second Run) (ohms)	Difference in Resistance (ohms)	Difference in Temperature (°K)
58.411	2.6618	2.6619	-0.0001	-0.002
69.604	3.3698	3.3697	+0.0002	+0.003
78.848	3.9559	3.9557	-0.0002	-0.003
87.353	4.4978	4.4969	+0.0009	+0.014
89.433	4.6302	4.6322	-0.0020	-0.032
89.461	4.6319	4.6313	-0.0023	-0.037
100.694	5.3519	5.3527	-0.0003	-0.012
109.395	5.9146	5.9143	+0.0003	+0.004
118.777	6.5271	6.5267	+0.0004	+0.006
127.267	7.0876	7.0876	-0.0000	-0.001
134.643	7.5799	7.5799	-0.0000	-0.003
142.842	8.1338	8.1335	+0.0003	+0.005
155.065	8.9723	8.9721	+0.0003	+0.004
161.242	9.4025	9.4023	+0.0002	+0.002
167.540	9.8456	9.8452	+0.0004	+0.005
175.575	10.4175	10.4179	+0.0003	+0.005
184.753	11.080	11.079	+0.0006	+0.003
191.116	11.547	11.547	+0.0008	+0.010
198.059	12.057	12.057	+0.0002	+0.003

Table II (cont'd)

Temperature (Second Run) (°K)	Resistance (From Curve Fits to First Run)	Resistance (Second Run) (ohms)	Difference in Resistance (ohms)	Difference in Temperature (°K)
208.151	12.814	12.814	-0.0001	-0.002
215.560	13.377	13.377	-0.0000	-0.000
222.147	13.883	13.883	+0.0006	+0.007
228.511	14.378	14.377	+0.0006	+0.008
256.445	16.608	16.608	+0.0002	+0.003
264.458	17.266	17.266	+0.0008	+0.010
272.605	17.943	17.943	+0.0002	+0.002
282.535	18.380	18.781	-0.0008	-0.009
289.851	19.404	19.405	-0.0010	-0.011

REFERENCES

James, B. W. and Yates, B., 1963. J. Sci. Inst., 40, 193.

Orlova, N. P., Astrov, D. N., and Medvedeva, L. A., 1964. Cryogenics, 4, 95.

White, G. K. and Woods, S. B., 1957. Rev. Sci. Inst., 28, 638.

White, G. K., Woods, S. B. and Anglin, F., 1958. Rev. Sci. Inst., 29, 181.

Yates, B. and Panter, C. H., 1961. J. Sci. Inst., 38, 196.

Chapter IV

DATA ANALYSIS

4.1 CURVE FITTING BY THE METHOD OF LEAST-MEAN-SQUARES

Measurements are always accompanied by errors, systematic errors and random errors. The former are due to inherent limits of sensitivity and defects in the calibration of equipment. It is often possible to discover the causes of these errors and, to some extent, to correct for them. Random errors are due to unknown causes but may be treated by statistical methods if they satisfy certain requirements. For the data with which we are concerned the requirement is that the distribution be Gaussian; that is, it must approximate the equation

$$w(x) = \frac{e^{-\frac{x^2}{2\sigma^2}}}{\sigma \sqrt{2\pi}}$$

or

$$N = \frac{h}{\pi} e^{-h^2 x^2} \quad (4.1)$$

where $w(x) = N$, $h^2 = \frac{1}{2\sigma^2}$, σ is the standard deviation, N is the frequency of a value occurring in a given interval and $x = (X_i - X)$ where X are the true values and X_i are the measured values.

In this work we make considerable use of the method of least-mean-squares to fit an equation to a set of data points determined by two variables. Curve fitting gives a smooth and continuous representation of physical quantities which had been determined at discrete intervals and the principle of least-mean-

squares provides a criterion for obtaining the most probable values of the measured quantities. Consider for example the simple case where n measurements have been taken, the i -th one having the error x_i . The probability that x_i lies between x_i and $x_i + dx_i$ is determined from (4.1) to be

$$P_i = \frac{h}{\pi} e^{-h^2 x_i^2} dx_i \quad (4.2)$$

Since each measurement is an independent event the probability of the occurrence of n errors $x_1, x_2, \dots, x_n$ is the product of n terms like (4.2). Hence,

$$P = \prod_{i=1}^n P_i = \left(\frac{h}{\pi} \right)^n e^{-h^2(x_1^2 + x_2^2 + \dots + x_n^2)} dx_1 dx_2 \dots dx_n$$

which is a maximum when the exponent of e is a minimum. We must therefore set

$x_1^2 + x_2^2 + \dots + x_n^2 = \text{a minimum, to obtain the most probable value of the quantity measured.}$

A method of doing the least-mean-squares fit of a polynomial to a set of discrete data is discussed by Hildebrand [30]. The goodness of fit is determined by the standard deviation

$$E_{\text{RMS}} = \left(\sum_{i=1}^n \left(\frac{R_i^2}{N - k} \right) \right)^{\frac{1}{2}}$$

where R_i is the residual at the i -th point, N is the number of points, and k is the number of coefficients. The standard error in each coefficient a_i is estimated by

$$(\sigma a_i)_{\text{RMS}} = A_{ii}^{\frac{1}{2}} E_{\text{RMS}}.$$

where A_{ii} is the i -th diagonal element of the inverse of the matrix of normal equations. A computer program based on the

above method was used extensively in the present work.

4.2 MEASUREMENTS OF THE STABILITY OF THE OSCILLATOR

The stability of the variable-frequency oscillator was determined by observing the variations in frequency when the sample was held at a constant temperature of 8°K. To simulate actual operating conditions these measurements were taken one every minute for two and a half hours. When the helium level was too high (near the top of the dewar) or too low (near the top of the expansion cell) a drift in frequency was observed. However in the intermediate range - permitting a running time of about two hours the drift was negligible. The data points (frequency versus time) from the intermediate region were fitted to a straight line by the method of least-mean-squares yielding an equation

$$F = FO + Bt \quad (4.3)$$

The standard deviation of points from this line was calculated to be 11.09 cps., and the maximum deviation was 20 cps. when the oscillator was operating at a frequency of about 40 mcs. The actual value of FO in (4.3) was $39,966,010 \pm 2.5$ cps., and the value of B (the drift coefficient) was $(1.05 \pm 5.17) \times 10^{-2}$ cps.- indicating a drift in frequency of only 1 ± 5 cps. over a period of about two hours. The data was further analyzed to determine whether the distribution of points about the average value given by (4.3) was Gaussian. For this purpose it was represented in the form of a histogram with an interval of one cycle per second. A normal curve was fitted to the histogram and Pearson's Chi-

square test indicated that the distribution was indeed Gaussian.

In practice several stability runs were made and in general the results were the same as for the above case. However, occasionally, the stability was about three to five times as bad as that stated above. It was also noticed that one set of measurements was much worse than the others. We are still uncertain as to the cause of this erratic behaviour.

Mechanical vibrations from within the building, and from the traffic outside are probably the main source of noise. Measurements of the level of vibrational noise in the laboratory have not been made and it is therefore not possible to establish if the occurrence of instability is due to vibrational noise. It has been observed that when the humidity is exceptionally high a considerable amount of snow gathers around the top of the nitrogen dewar and that some of it falls through the nitrogen to the bottom of the dewar. Hence it may be possible to attribute the unusually low stability to the effects of humidity. In any case a poor run is easily recognized and discarded.

4.3 TEMPERATURE DATA

Temperature measurements were made with a platinum resistance thermometer which was calibrated as described in Chapter III Section 3 - hence an equation

$$R = f(T) \qquad \langle 4.4 \rangle$$

was available. Readings of the potential drop across the thermometer and across a standard one ohm resistor were taken and converted by computer to values of resistance. From these it was necessary to determine the temperature, consequently an equation of the form

$$T = f(R)$$

would have been preferable. In practice this difficulty was overcome by a method of iteration by computer. A "trial temperature" T was set to be 13.000°K and inserted into $\langle 4.4 \rangle$, the resulting value of R was compared with the measured value R_M . If it was smaller than R_M the "trial temperature" was increased in steps of one degree until R became larger than R_M . Now T was decreased in steps of 0.10°K - and so on, until the agreement between R and R_M corresponded to a difference in temperature of 0.001°K or less. The values of temperature obtained in this way were punched on cards (by computer) and used for further calculations.

A great deal of effort was devoted to improving the accuracy in the measurements of temperature and the expected error

may now be quoted as about $\pm 0.01^\circ\text{K}$. The justification for this work becomes evident when we investigate the effect of an error in the temperature - $\text{er}(T)$ on the required results. For example, consider the effect of $\text{er}(T)$ on the ordinate $\frac{\Delta L}{LT^2}$ when equation (4.8) of section 4.5 is plotted in the form

$$\frac{\Delta L}{LT^2} = A + BT^2$$

If P_x is the probable error in a quantity X and P_y is the probable error in a quantity Y , then the probable errors in the values XY and $\frac{X}{Y}$ are given by Margenau and Murphy [33] as

$$P(XY) = \pm \sqrt{(XP_y)^2 + (YP_x)^2}$$

and

$$P\left(\frac{X}{Y}\right) = \frac{1}{y^2} \sqrt{X^2 P_y^2 + Y^2 P_x^2}$$

respectively. We may set $\frac{\Delta L}{L} = X$ and $T^2 = Y$. For copper at 10°K $X \approx 8 \times 10^{-8}$ and $Y = 10^2$, $P_x = 10^{-10}$ and $P_y = \sqrt{2} \times 10^{-1}$ (for $\text{er}(T) = 0.01^\circ\text{K}$) then $P\left(\frac{\Delta L}{LT^2}\right) \approx 10^{-4} \sqrt{1.28 \times 10^{-16} + 10^{-16}} = 0.15 \times 10^{-11}$ which corresponds closely with the value of the standard deviation of $\frac{\Delta L}{LT^2}$ calculated from the fit of $\frac{\Delta L}{LT^2}$ against T^2 . The first term under the square root sign is the contribution from $\text{er}(T)$, whereas the second term is the contribution from the error in the expansion measurements. We notice that both contribute equally to the total error. If however $\text{er}(T)$ was 0.10°K the equivalent expression would be

$$P\left(\frac{\Delta L}{LT^2}\right) \approx 10^{-4} \sqrt{1.28 \times 10^{-14} + 10^{-16}} \approx 0.11 \times 10^{-10}$$

and the error is due mainly to $\text{er}(T)$. At 15°K where $\frac{\Delta L}{L}$ is much larger, then the error $P\left(\frac{\Delta L}{LT^2}\right)$ is due mainly to $\text{er}(T)$ even for

er(T) as low as 0.01°K. At 4.2°K however, where the thermal expansion coefficient is very small

$$P \left(\frac{\Delta L}{LT^2} \right) \approx \frac{1}{256} \sqrt{18 \times 10^{-20} + 256 \times 10^{-20}}$$

for er(T) = 0.01°K and,

$$P \left(\frac{\Delta L}{LT^2} \right) = \frac{1}{256} \sqrt{18 \times 10^{-18} + 2.56 \times 10^{-18}}$$

for er(T) = 0.01°K. Hence, in our case the total error is due mainly to the limitation in sensitivity of the dilatometer. If however er(T) was greater than 0.03°K its contribution would be significant.

The above considerations emphasize that a statement of the sensitivity of a dilatometer alone does not indicate its quality. It is equally important to state the accuracy to which the temperature can be measured. Only if the above information is available is it possible to calculate the accuracy of the instrument for a given sample at a given temperature.

4.4 EXPANSION DATA

Values of frequency F were read directly from a frequency counter and related to the capacitance C by the equation

$$F = \frac{1}{2\pi} \left[\frac{C_1 C_2 + CC_2 + C_1 C_s + CC_s + C_1 C}{LC_2 (C_1 C_s + CC_s + C_1 C)} \right]$$

which is derived in Appendix I and there designated as (A 1.16). The value of C however is not a simple function of the spacing between the two plates and a correction for edge effects must be made even when a guard ring is employed. A formula due to Maxwell

and discussed by Hartshorn [34] gives

$$C = \frac{r^2}{4D} + \frac{rw}{4(D + 0.22w)} \left(1 + \frac{w}{2r} \right) \quad \langle 4.5 \rangle$$

where r is the radius of the central electrode P_2 , w is the spacing between the guard ring and plate P_2 and D is the gap between the capacitor plates P_1 and P_2 . The constants C_1 , C_2 and C_s were measured with a capacitance bridge to an accuracy of about 0.01%. The constants r and w were measured with a traveling microscope to an accuracy of 0.001 cm., that is to about 0.03% in r . To obtain the value of L , C was measured at 4.2°K with a capacitance bridge and the corresponding value of frequency was recorded - permitting the calculation of L from $\langle A\ 1.16 \rangle$. Substituting $\langle 4.5 \rangle$ into $\langle A\ 1.16 \rangle$ gives F as a function of D . In practice D is required as a function of F and this calculation was done to twelve figures in D by an iteration of the same type as described in the previous section. The values of the gap D along with the associated values of the temperature T were punched on cards (by computer) and are hereafter referred to as T.D. data.

4.5 ANALYSIS OF RESULTS

The T.D. data may be analyzed in several ways. It is possible to calculate the average linear thermal expansion coefficient α directly from the equation

$$\alpha = \frac{\Delta l}{L \Delta T} \quad \langle 4.6 \rangle$$

where ΔT is a discrete temperature change, Δl is the related change in length and L is the total length of the sample. For metals at low temperatures we expect on theoretical grounds that

$$\alpha = aT + bT^3 \quad \langle 4.7 \rangle$$

where the terms aT and bT^3 are due to the "pressure" of the electron gas and to the anharmonicity of the lattice vibrations respectively. This relation may be tested and the values of a and b determined by plotting $\frac{\alpha}{T}$ against T^2 . The total expansion per cm. from 0°K to a temperature T is given by $\frac{\Delta L}{L}$ and is simply the summation of all terms $\frac{\Delta L}{L}$. From $\langle 4.6 \rangle$

$$\frac{\Delta L}{L} = \int_0^T \frac{\alpha}{L} dT = \int_0^T \alpha dT$$

If $\langle 4.7 \rangle$ is valid then

$$\frac{\Delta L}{L} = AT^2 + BT^4 \quad \langle 4.8 \rangle$$

where $2A = a$ and $4B = b$. Alternately if $\langle 4.7 \rangle$ is valid we may measure $\frac{\Delta L}{L}$ and plot $\frac{\Delta L}{LT^2}$ against T^2 to determine A and B . Now α may be calculated from equation $\langle 4.7 \rangle$

In practice measurements are restricted to the range above 4.2°K and the curve $\langle 4.8 \rangle$ must be extrapolated to 0°K to give the correct value of ΔL . Another difficulty arises if the relation $\langle 4.7 \rangle$ is not strictly valid - then the values of α cannot be determined as indicated above. This method however has several advantages. It lends itself easily to determining values of α , A and B from T.D. data and the values of α are not average values as in the case of equation $\langle 4.6 \rangle$. The latter consideration is important at the lower temperatures where the expansion coefficients are usually small and vary rapidly. From $\langle 4.7 \rangle$ the ratio of the electronic to the lattice term is

$$\frac{aT}{bT^3} = \frac{a}{bT^2} = \frac{2A}{4BT^2} = \frac{A}{2BT^2}$$

whereas the corresponding ratio from (4.8) is

$$\frac{AT^2}{BT^4} = \frac{A}{BT^2} \quad - \text{ twice the above value.}$$

Consequently the second method gives the electronic term to greater accuracy.

In practice a , b , A and B in equations (4.7) and (4.8) are not determined graphically but numerically by the previously-discussed least-mean-squares program which also provides error estimates of these coefficients. This method has the advantage of speed and accuracy in computation. The values obtained, especially of the error estimates are unbiased for they do not rely on judgements of the eye as do graphical methods.

It is also important to determine whether the relation (4.7) is valid over the range where measurements were taken. The usual method is to fit the data (either graphically or by computer) to a curve and to decide from the scatter of points and from the standard deviation if the fit is good. A more reliable indication of the validity of (4.7) is obtained in the following way: Points between 4.2 and 8°K are used to obtain the first fit to equation (4.7) and to obtain the coefficients A_1 and B_1 . Then points between 4.2 and 9°K yield a second fit and the coefficients A_2 and B_2 , and so on, until all the points up to 15°K have been used. If A_i and B_i are approximately equal to A_1 and B_1 up to a temperature T and deviate from these values above T , then we may conclude that (4.7) is valid only to temperature T . Furthermore the variations between the values of A_i and B_i (in the region where (4.7) is valid) provide another indication of the accuracy to which A and B can be calculated from a given set of data.

Chapter V

RESULTS AND DISCUSSION

5.1 SPECIMENS

Measurements were done on three polycrystalline samples; namely, copper, silver and gold, and on one single crystal of copper. The first three were supplied by Johnson, Matthey and Co. and were quoted as being 99.999% pure, 99.999% pure and 99.997% pure respectively. The following impurities were found in the copper sample: iron ~ 2 ppm.; silver ~ 4 ppm.; silicon ~ 1 ppm.; cadmium < 1 ppm.; lead < 1 ppm.; and magnesium < 1 ppm. The impurities present in the silver were: iron ~ 5 ppm.; copper ~ 2 ppm.; cadmium < 1 ppm.; calcium < 1 ppm.; magnesium < 1 ppm.; and tin < 1 ppm. The impurities present in the gold were copper and silver with possible traces of selenium and tellurium.

The single crystal of copper was supplied by Semi-Elements, Inc. and was quoted as being 99.995% pure and oriented along the (1, 1, 1) axis. X-ray photographs taken in this laboratory verified that the sample was indeed a single crystal and confirmed the orientation to within several degrees of arc. All specimens were in the form of a rod about 7 mm. in diameter and 10 cm. long.

5.2 MEASUREMENTS ON POLYCRYSTALLINE COPPER BETWEEN 4.2 AND 15°K

5.2 (a) Purpose

There were two reasons for doing measurements on polycrystalline copper. First, it has been investigated by all workers doing measurements of thermal expansion between 4.2 and 15°K and is generally accepted as a reference. The measurements on copper could therefore be used to test the apparatus which we constructed. Secondly, theoretical calculations relating the electronic and lattice terms in the thermal expansion to the electronic and lattice terms in the specific heat were carried out by Collins [28] and [34], for copper, silver, and gold. Although excellent values of the electronic and lattice components of the specific heats of copper, silver and gold were obtained by Martin [35], no good measurements of the thermal expansion were available for gold in the low temperature range. The electronic component of the thermal expansion of silver was not available and the experimental results for the electronic component of copper appear to be in disagreement with the theoretical values. The table below (taken from Collins [28] and [34] gives the currently available information for copper, silver and gold, where γ_{∞} is the high temperature limiting value of γ , γ_0 is the low temperature limit of γ , and γ_e is the value associated with the electronic contribution.

Specimen	γ_{∞}		γ_0		γ_e	
	Theor.	Exp.	Theor.	Exp.	Theor.	Exp.
Copper	1.98	2.00	1.77	$1.69 \pm .05$	$1.01 \pm .1$	0.70 ± 0.20
Silver	2.40	2.4	2.22	$2.2 \pm .1$	0.94	-
Gold	3.04	$3.0 \pm .06$	2.92	-	1.23	-

TABLE I

A comparison of theoretical and experimental values of Gruneissen gammas for copper, silver and gold.

There appears to be some uncertainty concerning the values for copper since White's [36] most recent measurements on this element were published in 1964 yielding $\gamma_o = 1.72 \pm 0.03$ and $\gamma_e = 0.63 \pm 0.06$, whereas the values given in Table I were published by Collins in 1966. In any case it is of interest to determine with certainty whether the experimental values do, or do not support the theoretical work.

5.2 (b) Results for Polycrystalline Copper

The T.D. values obtained from measurements on copper were fitted to a polynomial of the form

$$D = A + BT + CT^2 + DT^3 + ET^4 + FT^5$$

The standard deviation in D was found to be about 1.2×10^{-9} . The change in the length of the ten centimeter sample was therefore known with an accuracy of about 1.2×10^{-10} cm./cm. for each point. Since 125 measurements were taken over the range investigated, the accuracy on the basis of statistical analysis is about 10^{-11} cm./cm.

The T.D. data were further analyzed according to the procedures outlined in section 4.4 and the results are presented in Table II for Run 1 and in Table III for Run 2. Table IV contains values which are the averages of those obtained for Runs 1 and 2. The values of a, b, and α were calculated from a fit of equation (4.8) to the T.D. data. That is, points from 4.2 to 8°K were fitted to equation (4.8) to yield the values of a and b given in row 4, columns 1 and 3. The value of α given in row 4, column 5 was derived from (4.7) using the above values of

a and b. When data to 9°K were included in the fit, the new values of a, b and α appearing in row 5, columns 1, 3 and 5 were obtained - and so forth. Equation (4.7) provided values of α_A when the a, and b in that equation were found by simply averaging the eight values of a and b given in columns 1 and 3. Hence for Run 1 (4.7) is

$$10^{10} \alpha_A = 1.516 T + 0.2788 T^3 \quad (5.1)$$

and for Run 2 it is

$$10^{10} \alpha_A = 1.580 T + 0.2713 T^3 \quad (5.2)$$

The values α_G were obtained by graphical interpolation of the values of α calculated from equation (4.6).

Temp. in °K	a ($\times 10^{10}$)	$\pm \Delta a$ ($\times 10^{10}$)	b ($\times 10^{11}$)	$\pm \Delta b$ ($\times 10^{11}$)	α ($\times 10^8$)	α_A ($\times 10^8$)	α_G ($\times 10^8$)
5						.424	.520
6						.688	.670
7						1.062	1.140
8	1.460	.042	2.812	.019	1.592	1.549	1.520
9	1.479	.028	2.802	.010	2.193	2.169	2.160
10	1.489	.022	2.797	.007	2.970	2.940	2.940
11	1.507	.017	2.790	.005	3.850	3.878	3.830
12	1.529	.016	2.782	.004	5.055	5.000	4.900
13	1.550	.014	2.775	.003	6.327	6.322	6.090
14	1.556	.014	2.774	.003	7.646	7.864	7.710
15	1.551	.012	2.775	.002	9.136	9.637	-

TABLE II

Experimental results for polycrystalline copper - Run 1

Temp. in °K	a (x10 ¹⁰)	±Δa (x10 ¹⁰)	b (x10 ¹¹)	±Δb (x10 ¹¹)	α (x10 ⁸)	α _A (x10 ⁸)	α _G (x10 ⁸)
5						.418	.510
6						.675	.690
7						1.041	1.010
8	1.528	.028	2.746	.022	1.568	1.515	1.400
9	1.616	.033	2.699	.012	2.137	2.119	2.020
10	1.619	.027	2.698	.009	2.891	2.870	2.830
11	1.602	.019	2.705	.005	3.820	3.784	3.760
12	1.594	.017	2.708	.004	4.942	4.876	4.760
13	1.582	.014	2.712	.003	6.202	6.164	6.270
14	1.560	.013	2.719	.002	7.761	7.663	7.590
15	1.543	.011	2.724	.002	9.678	9.390	9.490

TABLE III

Experimental results for polycrystalline copper - Run 2

Temp. in °K	$\bar{a}$ (x10 ¹⁰)	$\overline{\Delta a}$ (x10 ¹⁰)	$\bar{b}$ (x10 ¹¹)	$\overline{\Delta b}$ (x10 ¹¹)	$\bar{\alpha}$ (x10 ⁸)	$\bar{\alpha}_A$ (x10 ⁸)	$\overline{\Delta \alpha}_A$ (x10 ⁸)	$\bar{\alpha}_G$ (x10 ⁸)
5						0.421	0.006	0.51
6						0.681	0.013	0.68
7						1.052	0.021	1.08
8	1.494	0.068	2.779	0.066	1.580	1.532	0.034	1.46
9	1.547	0.137	2.751	0.103	2.165	2.144	0.050	2.09
10	1.554	0.130	2.748	0.099	2.930	2.905	0.070	2.8
11	1.555	0.095	2.748	0.085	3.835	3.831	0.094	3.80
12	1.562	0.065	2.745	0.074	4.998	4.939	0.124	4.83
13	1.566	0.032	2.744	0.063	6.264	6.244	0.158	6.18
14	1.558	0.004	2.746	0.055	7.703	7.764	0.201	7.65
15	1.547	0.008	2.749	0.051	9.407	9.515	0.247	9.49

TABLE IV

Averages of the values of a, b, α, α_A and α_G given in Tables II and III. The values of $\overline{\Delta a}$, $\overline{\Delta b}$, and $\overline{\Delta \alpha}_A$ are not averages of Δa, Δb & Δα_A but represent the differences between the values of a, b, and α_A taken from Run 1 and the corresponding values from Run 2.

The differences between the values α_A and α are sufficiently small to be accounted for entirely by the experimental errors in a and b. We may therefore conclude that equation (4.7) is valid to at least 15°K. The α_G are also in good agreement with α_A and α above 9°K, but tend to deviate from these values at lower temperatures where the accuracy of graphical methods is lower. In this region however the average values $\overline{\alpha_G}$ and $\overline{\alpha_A}$ are in fair agreement. As may be expected the standard errors Δa and Δb in a and b decrease as more and more data points are included in the calculations. It must be realized that these error limits take into account only the effects of random errors. They are properly used to intercompare values of a and b derived from the same run; however these error limits do not include the effects of systematic errors which can be best estimated by comparing values of a and b calculated from different runs. Hence in Table IV we find the error estimates $\overline{\Delta a}$, $\overline{\Delta b}$ and $\overline{\Delta \alpha_A}$ obtained from the difference between the corresponding values of Run 1, and Run 2; for example, the difference between the a appearing in row 4, column 1, of Table II and the a given in row 4, column 1 of Table III is $1.528 \times 10^{-10} - 1.460 \times 10^{-10} = 0.068 = \overline{\Delta a}$ which appears in row 4, column 2 of Table IV. This sort of simple calculation is of course only an indication of the systematic errors present and is in general a minimum value. A more realistic estimate would be about two or three times as high, while a truly reliable value can only be obtained by taking into account the work of several investigators using different techniques to perform the required measurements.

Calculations including all data points between 4.2 and

15°K yield

$$10^{10}\alpha = (1.551 \pm 0.012)T + (0.2775 \pm 0.0002)T^3 \quad \langle 5.3 \rangle$$

for Run 1, and

$$10^{10}\alpha = (1.543 \pm 0.011)T + (0.2724 \pm 0.0002)T^3 \quad \langle 5.4 \rangle$$

for Run 2, where the error limits take into account only random errors. In comparison, when the average values from row 11 of Table IV are used we have

$$10^{10}\alpha = (1.547 \pm 0.008)T + (0.2749 \pm 0.005)T^3 \quad \langle 5.5 \rangle$$

However the most reliable values of the coefficients are obtained by taking an average of the eight values $\bar{a}$ and $\bar{b}$ of Table IV to give

$$10^{10}\alpha = 1.547T + 0.2751T^3 \quad \langle 5.6 \rangle$$

In this case the selection of error limits for a and b is rather difficult. From Tables II and III the maximum deviations Δa are 3% and 2% respectively, and the deviations Δb are 0.7% and 0.7% respectively. When all the data points are used in the analysis the Δa are not at most 1% and 0.8%, and the Δb are at most 0.1% and 0.1%. From Table IV the maximum deviations $\overline{\Delta a}$ and $\overline{\Delta b}$ are 9% and 4%, whereas when points up to 15°K are included in the analysis the maximum deviations are only 0.5% and 0.2%. Choosing error limits of 3% and 1% we may use the values $a = 1.547 \pm 3\%$ and $b = 0.2751 \pm 1\%$ with considerable confidence.

The relation $\langle 5.6 \rangle$ is used in the following Table to generate values of α

Temp. in °K	$\alpha \times 10^9$ °K ⁻¹	$C \times 10^3$ cal. °K (g atom)	γ	$\alpha_L \times 10^9$ °K ⁻¹	$C_L \times 10^3$ cal. °K (g atom)	γ_L
3	1.21	0.803	0.99	0.74	0.304	1.74
4	2.38	1.385	1.23	1.76	0.720	1.75
5	4.21	2.240	1.35	3.44	1.408	1.75
6	6.87	3.440	1.42	5.94	2.442	1.74
7	10.52	5.063	1.49	9.43	3.899	1.73
8	15.32	7.181	1.53	14.08	5.851	1.72
9	21.44	9.878	1.56	20.05	8.385	1.71
10	29.05	1.324	1.57	27.51	1.157	1.70
11	38.31	1.738	1.58	36.61	1.555	1.69
12	49.39	2.238	1.58	47.53	2.038	1.69
13	62.44	2.841	1.58	60.43	2.624	1.65
14	77.64	3.555	1.57	75.47	3.322	1.63
15	95.15	4.398	1.55	92.83	4.148	1.60

TABLE V
Calculation of γ and γ_L

The specific heat data used in the above Table were taken from Martin [36]. The values of γ are calculated from

$$\gamma = \frac{3 \propto VK}{C}$$

where $V = 7.04 \text{ cm}^3$ and $K = 14.20 \times 10^{11} \text{ dyn./cm}^2$ as given by Overton and Gaffney [37]. C_L is obtained by subtracting from C the electronic specific heat $C_e = 1.663 \times 10^{-4}T \text{ cal K}^{-1} (\text{g atom})^{-1}$, and α_L is obtained by subtracting from α the electronic component of the thermal expansion $\alpha_e = 1.547T \text{ K}^{-1}$; finally

$$\gamma_L = \frac{3\alpha_L VK}{C_L}$$

From Table V the low temperature limiting value of γ_L is

$$\gamma_0 = 1.74 \pm 0.02$$

and from

$$\gamma_e = \frac{3\alpha_e VK}{C_e}$$

we obtain

$$\gamma_e = 0.67 \pm 0.02$$

Table VI presents a comparison of the relevant quantities as given by various investigators.

Source	$a \times 10^{10}$	$b \times 10^{11}$	γ_0	γ_e
Shapiro et al [38] {Ayrton strip and optical lever} (1964)	2.78 ± 0.25	0.310 0.008	1.95 ± 0.05	1.21 ± 0.13
Carr and Swenson [39] {Differen- tial transformer} (1964)	1.7 ± 0.5	0.29 ± 0.2	1.76	0.7
White et al. [36] {Capacitance bridge} (1964)				
(i) differential cell graphical analysis	1.34 ± 0.15	$0.280 \pm$ 0.014		
(ii) differential cell least-mean- squares analysis	1.47	0.268	1.72 ± 0.03	0.63 ± 0.06
(iii) Absolute cell graphical analysis	1.5 ± 0.03	$0.284 \pm$ 0.008		
This work	$1.547 \pm$ 0.046	$0.275 \pm$ 0.0027	1.74 ± 0.02	0.67 ± 0.02
Collins [28] and [34] Theoretical calculations (1966)			1.77	1.01 ± 0.10

TABLE VI

A comparison of the values of a , b , γ_0 and γ_e resulting from recent work by several investigators.

5.2 (c) Discussion

It is evident that the experimental work is in good agreement with the exception of the values given by Shapiro et al. Their method of calibration could however, have introduced large systematic errors into the measurements taken at low temperature. The present work is in excellent agreement with that of White et al. Both groups present values which are sufficiently accurate for us to conclude that the theoretical work of Collins is not supported by experiment. In fact the value $\gamma_e = 0.67$ is exactly that predicted on the basis of the free-electron theory.

The consequences of these results are not immediately evident. The possibility exists that a theory derived entirely on the assumption of a single-crystal model does not apply to a polycrystalline specimen. Certainly we cannot speak of a Fermi-surface in connection with a polycrystalline sample, yet calculations done on the assumption of a single-crystal model have often been verified by experiments on polycrystalline materials.

5.3 MEASUREMENTS ON A SINGLE CRYSTAL OF COPPER

5.3 (a) Purpose

The results of the previous section suggest that measurements on a single crystal of copper might resolve the discrepancy between theory and experiment. One could of course argue that each minute crystal of a polycrystalline metal has its own Fermi-surface and that measurements on a large sample simply reflect properties of the crystalettes and that these should be the same as for a large single crystal. Although this may be true at high

temperature where the mean free path of electrons is small, it may not necessarily be valid at low temperatures where the mean free path in single crystals of high purity is known to be of the order of several millimeters. Again, it is difficult to understand the significance of the concept of a Fermi-surface for crystals sufficiently small that the mean free path of the electrons is longer than the dimensions of the crystals, especially since the electrons leave and enter them from a variety of directions. Thus it appears that measurements on a single crystal could be valuable in answering the above queries.

5.3 (b) Results for a Single Crystal of Copper

The T.D. values obtained from measurements on a single crystal of copper were analyzed in exactly the same way as before, and the accuracy was determined to be the same as for measurements on polycrystalline copper. In this case however, four separate runs are presented in the following tables.

Temp. Deg. K	a $\times 10^{10}$	Δa $\times 10^{10}$	b $\times 10^{11}$	Δb $\times 10^{11}$	α $\times 10^8$	α_A $\times 10^8$	α_G $\times 10^8$
5							
6						.467	.442
7						.726	.736
8	3.074	.051	2.520	.023	1.536	1.075	1.064
9	3.128	.034	2.490	.013	2.097	1.530	1.475
10	3.158	.026	2.478	.009	2.794	2.105	2.018
11	3.144	.020	2.484	.006	3.652	2.216	2.780
12	3.114	.019	2.494	.005	4.686	3.677	3.690
13	3.066	.019	2.510	.004	5.913	4.704	4.710
14	2.994	.022	2.532	.004	7.367	5.911	5.975
15	2.878	.035	2.565	.006	9.089	7.315	7.540
						8.929	9.238

TABLE VII

Results of Measurements on a Single Crystal of Copper Run 1

Temp. Deg. K	a $\times 10^{10}$	Δa $\times 10^{10}$	b $\times 10^{11}$	Δb $\times 10^{11}$	α $\times 10^8$	α_A $\times 10^8$	α_G $\times 10^8$
5							
6						.482	.480
7						.750	.715
8	3.102	.039	2.628	.018	1.584	1.111	1.100
9	3.142	.025	2.606	.009	2.183	1.581	1.455
10	3.184	.021	2.588	.007	2.876	2.175	2.125
11	3.224	.017	2.571	.005	3.777	2.909	2.815
12	3.222	.015	2.572	.004	4.831	3.799	3.712
13	3.196	.014	2.580	.004	6.084	4.860	4.805
14	3.164	.014	2.590	.003	7.550	6.108	6.304
15	3.108	.016	2.606	.003	9.262	7.558	7.612
						9.227	9.345

TABLE VIII

Results of Measurements on a Single Crystal of Copper Run 2.

Temp. Deg. K	a $\times 10^{10}$	Δa $\times 10^{10}$	b $\times 10^{11}$	Δb $\times 10^{11}$	α $\times 10$	α_A $\times 10^8$	α_G $\times 10^8$
5						.479	.480
6						.744	.719
7						1.101	1.075
8	3.148	.031	2.600	.004	1.583	1.566	1.510
9	3.242	.024	2.550	.009	2.151	2.153	2.095
10	3.256	.019	2.543	.006	2.869	2.879	2.855
11	3.256	.015	2.544	.004	3.744	3.758	3.785
12	3.236	.014	2.550	.003	4.795	4.807	4.822
13	3.196	.014	2.514	.003	5.939	6.039	6.070
14	3.146	.016	2.580	.003	7.520	7.471	7.600
15	3.072	.019	2.601	.003	9.239	9.119	9.420

TABLE IX

Results of Measurements on a Single crystal of Copper Run 3.

Temp. Deg. K	a $\times 10^{10}$	Δa $\times 10^{10}$	b $\times 10^{11}$	Δb $\times 10^{11}$	α $\times 10$	α_A $\times 10^8$	α_G $\times 10^9$
5						.472	4.75
6						.734	6.85
7						1.088	10.10
8	2.862	.071	2.667	.033	1.595	1.548	14.20
9	3.180	.061	2.509	.022	2.115	2.131	20.25
10	3.204	.046	2.498	.015	2.818	2.851	27.85
11	3.202	.035	2.499	.010	3.678	3.723	37.80
12	3.178	.031	2.508	.008	4.715	4.763	47.39
13	3.122	.028	2.526	.006	5.956	5.986	60.30
14	3.044	.028	2.550	.005	7.423	7.408	76.00
15	2.954	.030	2.575	.005	9.134	9.043	93.75

TABLE X

Results of Measurements on a Single Crystal of Copper Run 4

We notice that again α and α_A are in good agreement with each other, hence equation (4.7) is again valid to at least 15°K

Table XI below gives the average values $\bar{a}$, $\bar{b}$, $\bar{\alpha}$, $\bar{\alpha}_A$ and $\bar{\alpha}_G$ of the corresponding quantities presented in the previous four Tables. However, the values of $\overline{\Delta a}$, $\overline{\Delta b}$, and $\overline{\Delta \alpha_A}$ are now the maximum deviations from the average of the four runs.

Temp. Deg. K	$\bar{a}$ $\times 10^{10}$	$\overline{\Delta a}$ $\times 10^{10}$	$\bar{b}$ $\times 10^{11}$	$\overline{\Delta b}$ $\times 10^{11}$	$\bar{\alpha}$ $\times 10^8$	$\bar{\alpha}_A$ $\times 10^8$	$\overline{\Delta \alpha_A}$ $\times 10^8$	$\bar{\alpha}_G$ $\times 10^8$
5						.875	0.008	.46
6						.738	0.012	.71
7						1.094	0.018	1.06
8	3.047	.185	2.604	.084	1.577	1.556	0.026	1.46
9	3.173	.069	2.539	.067	2.137	2.141	0.036	2.06
10	3.200	.056	2.527	.061	2.839	2.864	0.048	2.80
11	3.207	.053	2.525	.046	3.713	3.739	0.062	3.74
12	3.188	.074	2.531	.041	4.757	4.784	0.079	4.76
13	3.145	.079	2.533	.047	5.973	6.011	0.099	6.09
14	3.087	.093	2.563	.031	7.465	7.438	0.123	7.58
15	3.003	.125	2.587	.022	9.181	9.079	0.150	9.34

. TABLE XI

Averages of the values a , b , α , α_A and α_G given in Tables VII, VIII, IX and X. The values of $\overline{\Delta a}$, $\overline{\Delta b}$ and $\overline{\Delta \alpha_A}$ represent the maximum deviations from the average values $\bar{a}$, $\bar{b}$ and $\bar{\alpha}_A$.

Comparing the values in Table XI with those in the corresponding columns of Table IV it is evident that the $\bar{a}$ values are considerably larger than, and that the $\bar{b}$ values are

somewhat smaller than those given in Table IV. The maximum deviations from the mean $\overline{\Delta a}$, $\overline{\Delta b}$ and $\overline{\alpha_A}$ are of about the same magnitude as in Table IV.

In the following Table we give the values γ and γ_L for a single crystal of copper

Temp. in °K	$\alpha \times 10^8$ in °K ⁻¹	$C \times 10^2$ cal. °K ⁻¹ (g atom) ⁻¹	γ	$\alpha_L \times 10^8$ in °K ⁻¹	$C_L \times 10^2$ cal. °K ⁻¹ (g atom) ⁻¹	γ_L
3	0.163	0.080	1.46	0.069	0.030	1.63
4	0.289	0.139	1.50	0.163	0.072	1.63
5	0.475	0.224	1.52	0.319	0.141	1.63
6	0.738	0.344	1.54	0.551	0.244	1.62
7	1.094	0.506	1.55	0.875	0.390	1.61
8	1.556	0.718	1.55	1.306	0.585	1.60
9	2.141	0.988	1.55	1.860	0.838	1.59
10	2.864	1.324	1.55	2.551	1.158	1.58
11	3.739	1.738	1.54	3.395	1.555	1.57
12	4.784	2.738	1.53	4.408	2.038	1.55
13	6.011	2.841	1.52	5.605	2.625	1.53
14	7.438	3.555	1.50	7.000	3.322	1.51
15	9.079	4.398	1.48	8.610	4.149	1.49

TABLE XII

Values of γ and γ_L calculated from measurements of the thermal expansion of a single crystal of copper.

Proceeding as in section 5.2 (b) we have

$$10^{10}\alpha = (3.13 \pm 0.045)T + (0.2551 \pm 0.0025)T^3$$

$$\gamma_0 = 1.63 \pm 0.02$$

and

$$\gamma_e = 1.34 \pm 0.02$$

5.3 (c) Discussion

The results obtained from measurements on a single crystal of copper were most unexpected. The electronic component appears to be about twice as large as for polycrystalline copper, resulting in a γ_e which is now larger than the theoretical value and is again far outside the calculated error limits. Furthermore the value of γ_0 has decreased so that it is no longer in agreement with the theoretical result. These observations are difficult to reconcile with plausible arguments, however the following considerations will be further discussed:

1. The possibility of experimental error.
2. The effect of the orientation of the crystal in the (1,1,1) direction.
3. The effects of impurities.
4. The possibility of an inadequate interpretation of the linear term observed in the measurements of the thermal expansions and the specific heats of metals.

1. The possibility of a serious experimental error can of course, never be completely eliminated, however the greatest care and effort has been exercised in the design and use of the dilatometer.

Furthermore the excellent agreement of our measurements on polycrystalline copper and silver with the work of other investigators confirms the reliability of the apparatus used. Nevertheless independent measurements on a single crystal of copper (preferably employing a different method) would certainly do much to dispell any doubts concerning the validity of the results obtained.

2. The measurements were taken on a single crystal which was oriented along the (1,1,1) direction. Since the crystal lattice of copper is strictly cubic the thermal expansion, described by a second-rank tensor must necessarily be isotropic even though the Fermi-surface is somewhat distorted in certain directions. Consequently, it is very doubtful that the observed results could be due to the particular orientation chosen.

3. Certain impurities, in particular dilute solutions of about 0.56% and 0.23% manganese in copper have shown a measurable effect on the linear term in copper [40]. The purity of the single crystal was however quoted as 99.995% and it is very doubtful if 50 parts per million of any impurity could produce the drastic effect observed.

4. The interpretation of the linear term observed in measurements of the thermal expansions and the specific heats of metals has enjoyed considerable discussion. Theoretically difficulties arise when an attempt is made to include the possible influence of inter-electronic interactions. Daunt [41] writes "Theoretical

computations of C_e in the presence of exchange interaction have successfully been carried out by Bardeen [42], Wohlfarth [43], and Lidiard [44]; and Wohlfarth has shown, for example, that:

$$C_e = \frac{\Gamma T}{(a - b \ln T)}$$

where a and b are positive constants and Γ is the coefficient of the T term in the specific heat. For Na at liquid helium temperature, Wohlfarth estimated that marked deviations from the linear function of T should occur and that C_e should be about nine times smaller than the Sommerfeld value. Similar results were obtained by the other works, all stressing the great reduction in the absolute value of C_e due to the exchange forces.

On the other hand, the experimental Γ values for the metals of Group 1 to 4 all lie relatively near (within about a factor of 2) the Sommerfeld values and even the transition metals, which yield very high rather than very low Γ values in general, show no indication of deviations from the linear law of temperature dependence. Daunt further states, "The suggestion has been put forward by Wigner [45] that the inclusion of the effects of correlation forces would result in an increase in the density of states and so increases the value of C_e . Furthermore, he suggested that this increase was sufficient to compensate approximately for the decrease due to exchange interaction." Pines [46] has found that at least for the alkali metals the effects of exchange terms and correlation terms do cancel ~~approximately~~ as far as the specific heat evaluation is concerned, leaving the values of the coefficients of the linear term approximately the same as the electron values.

However he discovered [47] that there is not a similar cancelation when similar corrections are made to the free electron evaluation of the electronic paramagnetic susceptibility. It now appears that experimental observations of the linear term defy a rigorous theoretical explanation, and that a value of γ_e for a single crystal of copper may indeed be different from that obtained for a polycrystalline sample.

We must again consider the value $\gamma_e = 0.67$ obtained for polycrystalline copper. On theoretical grounds the electronic specific heat may be written [41] as

$$C_e = \Gamma T = \frac{2}{3} \pi^2 k^2 N(E_F) T \quad (5.7)$$

$$\text{where } N^*(E_F) = \frac{2\pi m^* V}{h^2} \left(\frac{3n}{\pi}\right)^{1/3} \quad (5.8)$$

and m^* and $N^*(E_F)$ become m and $N(E_F)$ for a free electron gas. For copper Γ is obtained experimentally and $\frac{m^*}{m}$ is calculated to be about 1.40. For the thermal expansion Varley [27] gives

$$\frac{C_e \gamma_e}{V} = \frac{C_e}{V} \left\{ 1 + \left(\frac{\partial \ln N(E_F)}{\partial \ln V} \right)_T \right\} \quad (5.9)$$

Substituting for C_e from (5.7) we have

$$\frac{C_e \gamma_e}{V} = \frac{2}{3V} \pi^2 k^2 N^*(E_F) T \left\{ 1 + \left(\frac{\partial \ln N(E_F)}{\partial \ln V} \right)_T \right\}$$

One would expect that for copper the $N(E_F)$ in expression (5.9) would be the same as the $N^*(E_F)$ appearing in (5.7) for the specific heat. However $\gamma_e = 2/3$ (experimental value for polycrystalline copper) is the case for a free electron gas, that is

for $m^* = m$. Hence there is a contradiction between the results obtained from specific heat and that obtained from thermal expansion. This is another indication that the experimental values obtained for a polycrystalline sample may not be adequately described by a single crystal model.

5.4 MEASUREMENTS ON SILVER AND GOLD

5.4 (a) Purpose

No reliable values of the thermal expansion of gold, below 15°K have yet been reported, and the only data available for silver in this range is the value $\gamma_0 = \gamma_L = 2.2 \pm .1$ (for $T < \frac{\theta}{20}$) published by White [48]. It is therefore interesting to obtain more information about these noble metals, for example, Martin [35] states, "Accurate measurements on the thermal expansion of gold in the region below 10°K might reflect the anomalous specific heat" (observed by him).

5.4 (b) Results for Polycrystalline Silver and Gold

The same type of data analysis was attempted for measurements on silver and gold as done on copper. However it was found that the equation

$$\alpha = aT + bT^3$$

was not valid even to 6°K . Consequently the electronic component could not be separated out from the lattice contribution. The thermal expansion coefficient was therefore calculated from

$$\alpha = \frac{dL}{L dt}$$

and is given in Table XIII for two sets of measurements on silver.

Temp. Deg. K	$\alpha \times 10^8$ Run 1	$\alpha \times 10^8$ Run 2	$\bar{\alpha} \times 10^8$	$\overline{\Delta\alpha} \times 10^8$
5	1.77	-	1.77	-
6	2.50	2.60	2.55	0.05
7	3.86	3.69	2.78	0.09
8	5.81	5.44	5.63	0.19
9	8.22	7.85	8.04	0.19
10	11.27	11.00	11.14	0.14
11	15.08	14.90	14.99	0.09
12	19.88	19.68	19.78	0.10
13	25.75	25.45	25.60	0.15
14	32.60	32.40	32.50	0.10
15	40.84	41.19	41.02	0.18

TABLE XIII

Results of Measurements on Silver Runs 1 and 2.

Since the total contraction from room temperature to 4.2°K of a rod of silver 10 cm. long is about 0.8×10^{-2} cm. greater than that of copper supports of equal length, it was necessary to use a gap of about 1.1×10^{-2} cm. between the capacitor plates as compared to the usual gap size of about 2.9×10^{-3} cm. This resulted in a decrease in the accuracy by a factor of about three as can be seen by comparing the $\overline{\Delta\alpha}$ values of silver with those of copper.

Since it was not possible to derive the electronic components for silver and gold it was also impossible to

calculate the true values of γ_L . However in these cases the electronic contribution is sufficiently small compared to the lattice component that, to a good approximation $\gamma \approx \gamma_L$ at low temperatures. A better value of γ_L can be obtained by assuming (a) that the electronic contribution can be accounted for by using the free electron value of γ_e , yielding $\gamma_L(\text{F.E.})$ (b) that the theoretical value of γ_e given by Collins can be assumed to hold, in this circumstance yielding $\gamma_L(\text{T})$. These values are presented in Table XIV below

Temp. Deg. K	$\alpha \times 10^8$ in $^{\circ}\text{K}^{-1}$	$C_V \times 10$ cal. $^{\circ}\text{K}^{-1}$ (g atom) $^{-1}$	γ	$\alpha_L(\text{F.E.})$ $\times 10^8$ $^{\circ}\text{K}^{-1}$	$C_L \times 10$ cal. $^{\circ}\text{K}^{-1}$ (g atom) $^{-1}$	γ_L (F.E.)	$\alpha_L(\text{T})$ $\times 10^8$ in $^{\circ}\text{K}^{-1}$	$\gamma_L(\text{T})$
5	1.77	.058	2.46	1.58	.050	2.53	1.50	2.38
6	2.55	.096	2.14	2.32	.086	2.16	2.22	2.07
7	3.78	.149	2.03	3.51	.138	2.04	3.40	1.98
8	5.63	.221	2.04	5.32	.209	2.04	5.20	1.99
9	8.04	.316	2.04	7.69	.302	2.04	7.55	2.00
10	11.14	.438	2.04	10.76	.422	2.04	10.60	2.01
11	14.99	.590	2.04	14.56	.573	2.04	14.39	2.02
12	19.78	.778	2.04	19.32	.759	2.04	19.13	2.02
13	25.60	1.007	2.04	25.10	.987	2.04	24.89	2.02
14	32.50	1.279	2.04	31.96	1.257	2.04	31.74	2.03
15	41.02	1.601	2.05	40.44	1.578	2.05	40.20	2.04

TABLE XIV

Calculations of γ and γ_L for measurements on polycrystalline silver.

It is obvious from the above Table that there is very little difference between γ and $\gamma_L(\text{F.E.})$ and $\gamma_L(\text{T})$.

For measurements on gold it was possible to adjust the size of the capacitor gap to the desired value, hence the accuracy of the results in the following Table is of the same magnitude as for copper.

Temp. Deg. K	α $\times 10^8$	$C_V \times 10$ cal. $^{\circ}\text{K}^{-1}$ (g atom) $^{-1}$	γ	$\alpha_L(\text{F.E.})$ $\times 10^8$ $^{\circ}\text{K}^{-1}$	$C_L \times 10$ cal. $^{\circ}\text{K}^{-1}$ (g atom) $^{-1}$	γ_L (F.E.)	$\alpha_L(\text{T})$ $\times 10^8$	γ_L (T)
5	2.55	.136	2.46	2.42	.126	2.52	2.31	2.41
6	4.62	.228	2.66	4.46	.217	2.70	4.33	2.62
7	7.53	.356	2.78	7.34	.344	2.88	7.19	2.82
8	11.42	.527	2.85	11.21	.513	2.87	11.03	2.82
9	16.45	.747	2.89	16.21	.732	2.91	16.01	2.87
10	22.75	1.030	2.92	22.48	1.013	2.91	22.26	2.88
11	30.62	1.382	2.91	30.33	1.363	2.92	30.08	2.90
12	39.71	1.806	2.89	39.39	1.775	2.91	39.12	2.89
13	50.02	2.303	2.85	49.67	2.280	2.86	49.38	2.84
14	61.80	2.877	2.82	61.43	2.853	2.83	60.74	2.80
15	77.38	3.523	2.89	76.98	3.497	2.89	76.65	2.89

TABLE XV

Results and calculations of γ and γ_L for polycrystalline gold

The $\gamma_L(\text{F.E.})$ calculated above was obtained by assuming that γ_e has the free electron value for gold, and the value $\gamma_L(\text{T})$ was obtained by again assuming the theoretical value of γ_e given by Collins. The values of γ , $\gamma_L(\text{F.E.})$ and $\gamma(\text{T})$ are again very similar, we may therefore use any one of the three as γ_L and we

$\alpha \times 10^{-8}$
($^{\circ}\text{K}^{-1}$)

Figure 10 Graph of α versus T
for silver-Run 1

Figure 13 Graph of $\frac{C_p}{T^3}$ and α_p versus T for gold (above) and silver (below)

chose $\gamma_L(\text{F.E.}) = \gamma_L$ for silver and gold. It is clear from the preceeding Tables that $\gamma_L(\text{F.E.})$ is approximately constant from 15°K down to about 8°K, it then increases rapidly for silver and decreases rapidly for gold. This variation can best be observed in a graph of $\frac{\gamma_L(\text{F.E.})}{T^3}$ versus T as given in Fig. 12.

If the constant part of $\gamma_L(\text{F.E.})$ is chosen as γ_0 , then we have $\gamma_0 = 2.04 \pm 0.06$ for silver and $\gamma_0 = 2.91 \pm 0.02$ for gold, which compare favourably with the theoretical values. $\gamma_0 = 2.22$ for silver and $\gamma_0 = 2.92$ for gold, and with the experimental result $\gamma_0 = 2.2 \pm 0.1$ obtained by White for silver.

5.4 (c) Discussion

The data for the thermal expansion of gold presented in the form of Fig. 13 yield the extremely interesting result that the anomalous increase of $\frac{C_L}{T^3}$ below 6°K in gold is accompanied by an anomalous decrease in $\frac{\alpha_L}{T^3}$. The anomalous increase in $\frac{\gamma_L}{T^3}$ for silver is just as surprising. It is now easy to understand why the data for silver and gold could not be represented by the sum of a linear and a cubic term in temperature. However the analysis resulting in Fig. 12 assumes that a linear electronic term can be subtracted, attributing the anomalous effect to the lattice alone. This may not be the case at all, indeed the anomalous behaviour might possibly be explained in terms of electron-phonon interactions.

Martin [35] has fitted his specific heat data to the equation

$$\frac{C - \gamma T}{T^3} = A + BT^2 + CT^4 \dots\dots\dots$$

and pointed out that the lattice specific heat can usually be approximated by the first two terms in the expansion at low

temperatures. He applied this method to silver and gold and found that the value of B might be negative for silver and that is is certainly negative for gold. For copper the method yields a positive value for B. He further suggested that B could be negative for copper if higher order terms such as CT^4 are included, and then points out that the copper results in particular, do not fit too well into the above method of analysis. He further states, "This equation assumes that the electronic and lattice specific heats may be treated separately but the electron-phonon interaction in a metal might alter the picture. De Launay showed that the free electrons probably participate completely in the motion of the ions for low-frequency vibrations but at higher frequencies the participation is negligible".

The negative values of B imply that at low temperatures the number of frequency modes increase with temperature more slowly than that predicted by Debye's theory. This in itself is unusual. In addition the results obtained herein for the thermal expansion of gold imply that the value of B must be positive, contradicting the specific heat data. The only alternative it seems, is to admit the presence of another term in either the expression for specific heat or in the expression for the thermal expansion or in both. The observed anomalous behaviour of the thermal expansion of silver would appear to support the above argument.

The experimental results obtained for the low temperature thermal expansions of silver and gold suggest that either inter-electronic or electron-phonon interactions, or both contribute significantly to the observed behaviour, and perhaps provide some

data on the basis of which further theoretical work can be initiated.

5.5 CONCLUSION

The measurements on a polycrystalline sample of copper verified the results of White and proved the reliability of the apparatus constructed. It was also shown that measurements on a polycrystalline sample of copper do not support the theoretical work of Collins.

Measurements on a single crystal of copper give significantly different values of the coefficients in equation (4.7) than were obtained for a polycrystalline sample. They therefore cast some doubt on the interpretation of the coefficient of the linear term in (4.7) suggesting that other interactions are involved.

Measurements on silver and gold suggest even more strongly that a considerable revision of the existing theory is required, and can perhaps guide the development of models taking into account the various interaction processes which occur in metals.

APPENDIX I

ANALYSIS OF THE OSCILLATOR CIRCUIT

The oscillator circuit of Fig. 6 may be represented by the four-terminal network Fig. A1. All stray capacitances except C_s are in parallel with either C_1 or C_2 and are included in the values of these capacitors. The oscillator tube is a constant-current generator, driven by a voltage V_G and producing a current $I_p = g_m V_g$, where g_m is the transconductance of the tube. Hence

$$g_m = \frac{I_p}{V_g} = \frac{I_p}{V_p} \cdot \frac{V_p}{V_g} = \frac{1}{Z_T} \cdot \frac{V_p}{V_g} \quad \langle A 1.1 \rangle$$

where
$$\frac{V_p}{V_g} = \frac{I_{C_o} Z'}{I_{C_1} Z_1}$$

$$\frac{I_{C_o}}{I_{C_1}} = \frac{I_{C_s} + I_{C_1}}{I_{C_1}}$$

and
$$\frac{I_{C_s}}{I_{C_1}} = \frac{Z_C + Z_1}{Z_s}$$

therefore:

$$\begin{aligned} \frac{V_p}{V_g} &= \frac{Z'}{Z_1} \left(1 + \frac{Z_C + Z_1}{Z_s} \right) \\ &= \frac{Z'}{Z_1} \left(\frac{Z_s + Z_C + Z_1}{Z_s} \right) \end{aligned} \quad \langle A 1.2 \rangle$$

We may now use the relations

$$\frac{1}{Z_T} = \frac{1}{Z_2} + \frac{1}{Z'} \quad \langle A 1.3 \rangle$$

FIG. A 1 FOUR TERMINAL REPRESENTATION
OF THE OSCILLATOR CIRCUIT

where

$$Z' = Z_L + Z'' \quad \langle A 1.4 \rangle$$

and

$$\frac{1}{Z''} = \frac{1}{Z_S} + \frac{1}{Z_C + Z_1} \quad \langle A 1.5 \rangle$$

where

$$Z_C = \frac{1}{j\omega C}, \quad Z_1 = \frac{1}{j\omega C_1}, \quad Z_S = \frac{1}{j\omega C_S}, \quad Z_L = R + j\omega L \quad \langle A 1.6 \rangle$$

Substituting from $\langle A 1.6 \rangle$ into $\langle A 1.5 \rangle$ yields.

$$\begin{aligned} \frac{1}{Z''} &= j\omega C_S + \frac{j\omega C C_1}{(C_1 + C)} \\ &= \frac{j\omega (C_S C_1 + C_S C + C C_1)}{(C_1 + C)} \\ &= \frac{j\omega \xi}{(C_1 + C)} \end{aligned} \quad \langle A 1.7 \rangle$$

$$\text{where } \xi = (C_S C_1 + C_S C + C C_1) \quad \langle A 1.8 \rangle$$

From $\langle A 1.4 \rangle$

$$\begin{aligned} Z' &= R + j\omega L - \frac{j(C_1 + C)}{\omega \xi} \\ &= \frac{R\omega \xi + j\omega^2 L \xi - j(C_1 + C)}{\omega \xi} \end{aligned} \quad \langle A 1.9 \rangle$$

From $\langle A 1.3 \rangle$

$$\begin{aligned} \frac{1}{Z_T} &= j\omega C_2 + \frac{\omega \xi}{R\omega \xi + j[\omega^2 L \xi - (C_1 + C)]} \\ &= \frac{\omega \xi - \omega C_2 [\omega^2 L \xi - (C_1 + C)] + jRC_2 \omega^2 \xi}{R\omega \xi + j[\omega^2 L \xi - (C_1 + C)]} \end{aligned}$$

$$= \frac{\omega \xi - \omega C_2 r + j R C_2 \omega^2 \xi}{R \omega \xi + j r}$$

$$\text{where } r = [\omega^2 L \xi - (C_1 + C)] \quad \langle A 1.10 \rangle$$

therefore

$$\frac{1}{Z_T} = \frac{R \omega^2 \xi^2 + j R^2 C_2 \omega^3 \xi^2 - j \omega \xi r + j \omega C_2 r^2}{R^2 \omega^2 \xi^2 + r^2} \quad \langle A 1.11 \rangle$$

Substituting $\langle A 1.9 \rangle$ into $\langle A 1.2 \rangle$ and making use of $\langle A 1.8 \rangle$ and making use of $\langle A 1.8 \rangle$ and $\langle A 1.10 \rangle$ yields

$$\begin{aligned} \frac{V_p}{V_g} &= \frac{[R \omega \xi + j \omega^2 L \xi - j(C_1 + C)] (C C_1 + C C_s + C_1 C_s)}{\omega \xi \left(\frac{1}{j \omega C_s} \right) \left(\frac{1}{j \omega C_1} \right) j \omega C_s C C_1} \\ &= \frac{\{j \omega R \xi - [\omega^2 L \xi - (C_1 + C)]\} (C C_1 + C C_s + C_1 C_s)}{\xi C} \\ &= \frac{1}{C} [j \omega R \xi - r] \quad \langle A 1.12 \rangle \end{aligned}$$

Substituting $\langle A 1.11 \rangle$ and $\langle A 1.12 \rangle$ into $\langle A 1.1 \rangle$ gives

$$\begin{aligned} g_m &= \frac{I_p}{V_g} \\ &= \frac{1}{C} \frac{[j \omega R \xi - r] [R \omega^2 \xi^2 + j R^2 C_2 \omega^3 \xi^2 - j \omega \xi r + j \omega C_2 r^2]}{R^2 \omega^2 \xi^2 + r^2} \quad \langle A 1.13 \rangle \end{aligned}$$

This is the loop equation for the circuit of Fig. 6. The transconductance of the oscillator tube is real and positive; it is therefore found by taking the real part of $\langle A 1.13 \rangle$. To obtain the condition for resonance Barkhausen's phase shift

criterion must be satisfied, that is the total phase shift around the oscillating loop must be zero and the gain must be unity. This criterion permits us to calculate the resonant frequency of the circuit from equation (A 1.13) by setting

$$\frac{\text{Imaginary part}}{\text{Real part}} = \tan \theta = 0 \quad (\text{or } 360^\circ)$$

Hence from (A 1.13)

$$[R^2 \omega^2 \xi^3 - R^2 C_2 \omega^2 \xi^2 \eta + \xi \eta^2 - C_2 \eta^3] = 0$$

therefore

$$\omega^2 R^2 \xi^2 [\xi - C_2 \eta] + \eta^2 [\xi - C_2 \eta] = 0$$

therefore

$$[\xi - C_2 \eta][\omega^2 R^2 \xi^2 + \eta^2] = 0$$

One possible mode of oscillation occurs when

$$[\omega^2 R^2 \xi^2 + \eta^2] = 0$$

that is when

$$\omega^2 R^2 \xi^2 + [\omega^2 L \xi - (C_1 + C)]^2 = 0$$

$$\text{i.e.} \quad \omega^4 L^2 \xi^2 - \omega^2 [2L\xi(C_1 + C) - R^2 \xi^2] + (C_1 + C)^2 = 0$$

therefore

$$\omega^4 - \omega^2 \left[\frac{2(C_1 + C)}{L\xi} - \frac{R^2}{L^2} \right] + \frac{(C_1 + C)^2}{L^2 \xi^2} = 0 \quad \text{(A 1.14)}$$

Comparing the magnitudes of the coefficients of ω^2 for typical values of C_1 , C , L , ξ and R we find

$$\frac{2(C_1 + C)}{L\xi} \approx 10^{14}$$

while $\frac{R^2}{L^2} \approx 10^2$ and may therefore be neglected with respect to the other term. Solving (A 1.14) for ω^2 yields

$$\begin{aligned}\omega^2 &= \frac{(C_1 + C)}{L\xi} \pm \frac{1}{2} \left[\frac{4(C_1 + C)^2}{L^2\xi^2} - \frac{4(C_1 + C)^2}{L^2\xi^2} \right]^{\frac{1}{2}} \\ &= \frac{(C_1 + C)}{L\xi} \\ &= \frac{C_1 + C}{L(C_1C_s + CC_s + CC_1)}\end{aligned}\quad (A\ 1.15)$$

The physical significance of this equation becomes evident when we make the approximation that $C_1 \gg C$ and $C_s \ll C$. In this case

$$\omega^2 = \frac{C + C_1}{LCC_1}$$

which is clearly the case for a series connection of the L - C circuit to the tube.

A second possible mode of oscillation occurs when

$$[\xi - C_2\eta] = 0$$

that is when

$$\omega^2 L\xi - (C_1 + C) = \frac{1}{C_2} \xi$$

$$\begin{aligned}\text{hence } \omega^2 &= \frac{(C_1 + C) + \frac{1}{C_2} \xi}{L\xi} \\ &= \frac{C_1C_2 + CC_2 + C_1C_s + CC_s + C_1C}{LC_2 (C_1C_s + CC_s + C_1C)}\end{aligned}\quad (A\ 1.16)$$

This is the mode which corresponds to a parallel resonance connection of the L - C circuit to the tube. In practice this

is the mode employed to do the required measurements.

APPENDIX II

DERIVATION OF THE GRUNEISEN RELATIONS

The Grⁱüneisen relations

$$\frac{\beta_L}{X} = \frac{\gamma_L C_L}{V} \quad \langle A \ 2.1 \rangle$$

and

$$\frac{\beta_e}{X} = \frac{\gamma_e C_e}{V} \quad \langle A \ 2.2 \rangle$$

representing the lattice and electronic components respectively, may be derived as follows:

The coefficient of volume expansion β and the compressibility X of a solid are defined as

$$\beta = \frac{1}{V} \left(\frac{\partial V}{\partial T} \right)_P \quad \langle A \ 2.3 \rangle$$

and

$$X = - \frac{1}{V} \left(\frac{\partial V}{\partial P} \right)_T \quad \langle A \ 2.4 \rangle$$

hence

$$\frac{\beta}{X} = - \left(\frac{\partial V}{\partial T} \right)_P \bigg/ \left(\frac{\partial V}{\partial P} \right)_T \quad \langle A \ 2.5 \rangle$$

From the "Table of Thermodynamics Relations" given by Slater [19]

$$\left(\frac{\partial S}{\partial V} \right)_T = \left(\frac{\partial P}{\partial T} \right)_V = - \left(\frac{\partial V}{\partial T} \right)_P \bigg/ \left(\frac{\partial V}{\partial P} \right)_T \quad \langle A \ 2.6 \rangle$$

It follows from $\langle A \ 2.6 \rangle$ and $\langle A \ 2.5 \rangle$ that

$$\frac{\beta}{X} = \left(\frac{\partial S}{\partial V} \right)_T \quad \langle A \ 2.7 \rangle$$

The total entropy may be divided into two parts, S_e , the entropy contribution from the valence electrons, and S_L , the contributions from the thermal vibrations of the atoms of the crystal. Thus

$$\frac{e}{X} = \left(-\frac{\partial S_L}{\partial V} \right)_T + \left(-\frac{\partial S_e}{\partial V} \right)_T \quad \langle A \ 2.8 \rangle$$

The Helmholtz free energy is defined as

$$F = U - TS_L$$

hence

$$dF = dU - TdS_L - S_LdT$$

For a reversible process

$$dw = TdS - dU$$

therefore

$$dF = -dw - S_LdT$$

and

$$\left(\frac{\partial F}{\partial T} \right)_V = -S_L$$

consequently

$$\frac{B_L}{X} = \left(-\frac{\partial S_L}{\partial V} \right)_T = \frac{\partial^2 F(v, T)}{\partial V \partial T} \quad \langle A \ 2.9 \rangle$$

where

$$F(v, T) = U_0 + \sum_{i=1}^{3N} \frac{1}{2} \hbar \omega_i(V) + kT \sum_{i=1}^{3N} \ln \left(1 - e^{\frac{-\hbar \omega_i}{kT}} \right)$$

The above expression for the Helmholtz free energy is obtained from Statistical Mechanics as follows:

THE YMCA CLARION

No. 5-June 5th.1933

PUBLISHED BY STUDENTS ALUMNI AND CITIZENS.

READ TO THE BOARD OF DIRECTORS BY REQUEST JUNE 5.

This committee appointed by the Clarion group appreciates the opportunity to come before you today to review in part its point of view of the "Y" School question.

It is almost needless to state again that this group has the utmost respect for this Board of Directors, both individually and collectively. We recognize fully that this Board, like members of our own group, is giving its time generously and unselfishly to the Y M C A, and like members of our own group, is sincerely devoted to the best interests of this great institution.

We have never claimed that the Board of Directors was not qualified to decide school matters, but we have maintained from the outset that it is not apparent that the Board has received all the information that it should have received bearing on the school question before it took this action.

When those many hundreds of us immensely interested in "Y" work learned of the intention to close the schools, we were astonished at the action of the Board. The first impression we got from that action was that the Board was misinformed or it would not have taken action.

Our first step planned was to investigate and prepare statements for this Board so that they could see the great values that come from the School's programs so that in discussion and voting they could do so intelligently. However, in our investigations, which have been many, we found so many underlying currents, all hinging on school matters, that after consulting a great number of people, educators, supporters and friends of the "Y", we began to find, in our opinion, what we think was a deliberate attempt to abolish the schools. We believe there is ample proof of the idea that Mr. McKim has entertained ideas, and has expressed them, for 6 years past to abolish the "Y" schools just as soon as he could do so. That he has done practically nothing for 6 years or so to aid in their growth and development. What business represented by members of this Board would grow and prosper if the Executive head was determined or willing to see it die. With the finding of these facts, it is no wonder the Board, whom we feel have been sold by Mr. McKim on the closing of the Schools, has closed the schools.

The Board must, out of necessity, depend on its General Secretary to keep them advised of the "Y" activities. Is it any wonder then if the General Secretary does not like the schools, that he would recommend their discontinuance. With such a viewpoint he would sincerely sell the Board to close the schools.

We have never pretended that students, or faculty, members or the Educational Director, should be consulted for advice, but we have and do contend that they and the National Office should be consulted for information. The students were consulted for information a year ago by a committee consisting of Messrs. Morrison, Marx and Hicks. We quote from the report which they made a year ago last April. (See page #9)

Taking the logarithm

$$-\frac{F}{kT} = -\sum_j \frac{(\frac{1}{2}h\nu_j + U_0)}{kT} - \sum_j \ln \left(1 - e^{-\frac{h\nu_j}{kT}} \right)$$

therefore

$$F(v, T) = U_0 + \sum_j \frac{1}{2}h\nu_j + \sum_j kT \ln \left(1 - e^{-\frac{h\nu_j}{kT}} \right) \quad \langle A \ 2.12 \rangle$$

Taking the partial derivatives with respect to T and V we obtain

$$\frac{\partial F(v, T)}{\partial T} = k \sum_{j=1}^{3N} \ln \left(1 - e^{-\frac{h\nu_j(v)}{kT}} \right) + kT \sum_{j=1}^{3N} \frac{-\frac{h\nu_j}{kT}}{\left(e^{-\frac{h\nu_j}{kT}} - 1 \right)}$$

and

$$\begin{aligned} \frac{\partial F(v, T)}{\partial V \partial T} = & \left\{ k \sum_{j=1}^{3N} \frac{-\frac{h}{kT}}{\left(e^{-\frac{h\nu_j}{kT}} - 1 \right)} + kT \sum_{j=1}^{3N} \frac{-\frac{h}{kT^2}}{\left(e^{-\frac{h\nu_j}{kT}} - 1 \right)} \right. \\ & \left. + kT \sum_{j=1}^{3N} \frac{-\frac{h\nu_j}{kT^2} \times \frac{h}{kT} e^{-\frac{h\nu_j}{kT}}}{\left(e^{-\frac{h\nu_j}{kT}} - 1 \right)^2} \right\} \frac{\partial \nu}{\partial V} \end{aligned}$$

therefore

$$\begin{aligned} \frac{\partial^2 F(v, T)}{\partial V \partial T} &= \frac{1}{V} \sum_{j=1}^{3N} k \left(\frac{h\nu_j}{kT} \right)^2 \frac{e^{-\frac{h\nu_j}{kT}}}{\left(e^{-\frac{h\nu_j}{kT}} - 1 \right)^2} \frac{\partial \ln \nu}{\partial \ln V} \\ &= \frac{1}{V} \sum_{j=1}^{3N} \gamma_j C_j = \frac{\beta_L}{\bar{\chi}} \quad \langle A \ 2.13 \rangle \end{aligned}$$

$$\text{where } C_j = k \left(\frac{h\nu_j}{kT} \right)^2 \frac{e^{-\frac{h\nu_j}{kT}}}{\left(e^{-\frac{h\nu_j}{kT}} - 1 \right)^2} \quad \langle A \ 2.14 \rangle$$

is the contribution of the j^{th} mode to the specific heat $C_{V(L)}$, and

$$\gamma_j = \frac{\partial \ln \nu_j(V)}{\partial \ln V} \quad \langle A 2.15 \rangle$$

The relationship $\langle A 2.15 \rangle$ may be obtained from the variation of the vibrational frequencies of the lattice with volume. It is reasonable to assume that, as the volume of a solid is decreased the vibrational frequencies will increase since both changes are related to an increase in the energy of the system. Thus the ν_i vary as some function of V . Assuming that

$$\nu_i = \frac{C_i}{V^{\gamma_i}}$$

where C_i is some constant, we have

$$\ln \nu_i = \ln C_i - \gamma_i \ln V$$

therefore

$$\frac{d \ln \nu_i}{d \ln V} = -\gamma_i$$

Now if all the γ_i are equal (as in the Debye theory), it follows from $\langle A 2.13 \rangle$ that

$$\beta_L = \gamma_L \frac{X}{V} C_L$$

which is the first Grüneisen relation $\langle A 2.1 \rangle$.

Let us now consider the effect of the electrons.

Slater [19] has shown that the entropy contribution S_e , arising from the electrons is given by

$$S_e = \frac{\pi^2}{3} k^2 T V n(\epsilon_F) \quad \langle A 2.16 \rangle$$

where $\eta(\epsilon_F)$ is the total density of states per unit volume of crystal over all partially filled bands evaluated at the Fermi energy ϵ_F . Differentiating (A 2.16) with respect to volume at constant temperature gives

$$\left(\frac{\partial S_e}{\partial V} \right)_T = \frac{\pi^2}{3} kT \eta(\epsilon_F) \left\{ 1 + \left(\frac{\partial \ln \eta(\epsilon_F)}{\partial \ln V} \right)_T \right\} \quad \text{(A 2.17)}$$

Furthermore, the electronic specific heat at a constant volume is given by

$$C_e = T \left(\frac{\partial S_e}{\partial T} \right)_V$$

Substituting into (A 2.17) gives

$$\begin{aligned} \left(\frac{\partial S_e}{\partial V} \right)_T &= \frac{C_e}{V} \left\{ 1 + \left(\frac{\partial \ln \eta(\epsilon_F)}{\partial \ln V} \right)_T \right\} \\ &= \frac{C_e}{V} \gamma_e \end{aligned}$$

which is the second Grüneisen relation (A 2.2), when

$$\gamma_e = \left[1 + \left(\frac{\partial \ln \eta(\epsilon_F)}{\partial \ln V} \right)_T \right]$$

In general however, $\eta(\epsilon_F)$ is an explicit function of the Fermi energy and of the volume, hence

$$\left(\frac{\partial \eta(\epsilon_F)}{\partial V} \right)_T = \left(\frac{\partial \eta(\epsilon_F)}{\partial \epsilon_F} \right)_{V,T} \left(\frac{\partial \epsilon_F}{\partial V} \right)_T + \left(\frac{\partial \eta(\epsilon_F)}{\partial V} \right)_{\epsilon_F,T}$$

For this case Varley [27] shows that

$$\gamma_e = \left\{ 1 + \left(\frac{\partial \ln n(\epsilon_F)}{\partial \ln V} \right)_{\epsilon_F, T} - \frac{N}{n(\epsilon_F)^2} \left(\frac{\partial n(\epsilon_F)}{\partial \epsilon_F} \right)_V \left(1 + \frac{\partial \ln N}{\partial \ln V} \right)_{\epsilon_F, T} \right. \\ \left. + \frac{C_e}{\alpha V n(\epsilon_F)^3} \left(\frac{\partial n(\epsilon_F)}{\partial \epsilon_F} \right)_V^2 \right\}$$

REFERENCES

1. Born, M. and von Karman
Th. Z. Phys. 13(1912) 297
2. Debye, P. P.
Ann. Phys. Lpz. 39(1912) 789
3. Born, M. and Oppenheimer, R.
Ann. Phys., Lpz. 84(1927) 457
4. Blackman, M.
Proc. R. Soc. A148(1935) 365, 384; 149(1935)
117, 126; 159(1937) 416; 164(1938) 62
5. Smith, H. M. J.
Phil. Trans. R. Soc. A241(1948) 105
6. Kellerman, E. W.
Phil. Trans. R. Soc. A238(1940) 513
7. Houston, W. H.
Rev. mod. Phys. 20(1948) 161
8. Montroll, E. W.
J. Chem. Phys. 10(1942) 218; 11(1943) 481;
12(1944) 98 (with Peaslee, D.)
9. Leighton, R. B.
Rev. mod. Phys. 20(1948) 165
10. van Hove, L.
Phys. Rev. 89(1953) 1189

11. Montroll, E. W.
Proc. Third Berkeley Symposium on Math. Statistics and
Probability. Univ. of California Press (1955) 209
12. Phillips, J. C.
Phys. Rev. 104(1956) 1263; J. Phys. Chem. Solids
5(1958) 288 (with Rosenstock, H.B.)
13. Rosenstock, H. B.
Phys. Rev. 97(1955) 290; J. Phys. Chem. Solids
2(1957) 44
14. Brockhouse, B. N. and Stewart, A. T.
Rev. mod. Phys. 30(1950) 236;
Brockhouse, B. N. and Iyengar, P. K. Phys. Rev. 111(1958)
747
15. Cochran, W.
Proc. R. Soc. A253(1959) 260
16. White, H. C.
Phys. Rev. 112(1958) 1092
17. Varshni, Y. P. and Shukla R. C.
J. Chem. Phys. 43(1965) 488
18. Grüneisen, E.
Handbuch der Physik, 10(1926) 1
19. Slater, J. C.
Introduction to Chemical Physics, 1939. New York,
McGraw-Hill

20. Bijl, D. and Pullon, H.
Phil. Mag. 45(1954) 290, and Physica' 21(1955) 285
21. Barron, T. H. K.
Phil. Mag. 46(1955) 720
22. Pippard, A. B.
Phil Trans. A250(1957) 325
23. Shoenberg, D.
Phil Mag. 5(1960) 105
24. Alekseevski, N. E. and Gaidukov, X. P.
J. Exp. Theor. Phys. Moscow, 37(1959) 672
25. Langenberg, D. N. and Moore, T. W.
Phys. Rev. Letters. 3(1959) 328
26. Gavenda, J. D., and Morse, R. W.
Bull. Amer. Phys. Soc. 4(1959) 463
27. Varley, J. H. O.
Proc. Roy. Soc. (London), A237(1956) 413
28. Collins, J. G.
Ann. Acad. Sci. Fennicae. A VI(1966) 210
29. Templeton, I. M.
Proc. Roy. Soc. (London), to be published
30. Clapp, J. K.
Proc. I.R.E. March (1948) 356

We now quote from statements made from Y M C A sources outside of Cincinnati:

"One of the outstanding educators of the country said recently to one of the larger foundations that they ought to support the Y M C A Schools (he was speaking particularly of liberal arts and secondary schools) because they were free to experiment and pioneer in developing new programs and using new methods, and in pointing the way for other educational institutions. He told the foundation that what it put into Y M C A Schools would have a larger effect upon public and collegiate education than if they put the same amount in a public school or a teachers' college, or in endowment of a certain group of public educators."

"Where the Y M C A has made a systematic effort to develop distinctive and worthwhile educational programs and, at the same time, to properly interpret its program to the community, particularly the educational leaders, there is practically no criticism from the standpoint of competition or duplication. A good Y M C A school does more than offer standard courses in subject matter. It helps young men and adults gain the technical knowledge and skills that they need for their occupations or their general educational advance. But it goes further. It helps young men understand themselves. It helps them gain a better understanding of the world in which they live. It helps them learn how to get along with each other. It sensitizes them to social and ethical values beyond the limits of technical subject matter. It helps them develop an open-minded philosophy of life in the light of Christian ideals. The outcomes of a good school are comparable to the outcomes of an all-round Association program. In fact, recent studies show that the extraclass activities of a Y M C A school are as broad and varied as is the total program of a typical central branch. An Association, then, needs to think of its school not simply as technical or academic subjects accredited by educators in which young men pay the fees, the Association should regard the school as it does any other Association program, except that young men come into it with primary interests in education rather than primary interests in recreation, as they do now into an Association built around a gymnasium. A school is a door through which men come. The program in the school on the surface may look somewhat different from the program of a more typical branch built around a gymnasium, but it should not be any less varied. It should be no less broad and it should accomplish no less worthy outcomes in the lives of the persons enrolled."

"One can find in the Association an occasional secretary or an occasional layman who still thinks that the Association should practically give up its formal educational work. The argument cannot be based upon the subsidy requirement cost, for the cost is smaller than any other program that the Association conducts. The argument cannot be intelligently based upon the outcomes not being worthwhile for a study of what happens to students attending Y M C A schools shows that the changes in the lives of persons are quite typical of what happens in other good Association programs. The argument cannot be based upon the lack of demand, for leaders of education today are demanding more adult education. The most recent pronouncement of the most distinguished educators of this country point to adult education as the greatest need of the coming years. Perhaps the next ten years will see a larger demand for adult education than any other period of American History. The Association with its long experience in this field stands in a position to render a distinctive service and to point the way to other agencies. The field is not overcrowded with outstanding and well equipped adult education institutions. Some Association schools, as well as some other adult education agencies, may go out of existence in the next few years because of their lack of understanding of the situation, or because of their inability to meet these needs, or perhaps because of their desire to give attention to some other things. They need not go out of existence because of the lack of opportunity. But these same things might be said about any phase of the Association program. In some places boys' work is being given up, partly because the cost is too much, in other places where the Association thinks there is no demand for it. On the basis of what the Association is doing in the field of religious education one might assume there is no more need for religion. And there are those who would say that recreation and health has been taken over by other agencies. An Association may rationalize it-

- 40 White, G. K.
J. Phys. Chem. Solids 23(1962) 169
41. Daunt, J. G.
Progress in Low Temperature Physics Vol I
pp. 202 - 223 North-Holland Publishing Co.
- 42 Bardeen, J.
Phys. Rev. 50(1936) 1098
- 43 Wohlfarth, E. P.
Phil. Mag. 41(1950) 534
- 44 Lidiard, A. B.
Phil. Mag. 42(1951) 1325
45. Wigner, E.
Trans. Faraday Soc. 34(1938) 678
46. Pines, D.
Phys. Rev. 92(1953) 626
47. Pines, D.
Phys. Rev. 95(1954) 1090
48. White, G. K.
Proc. 8th Int. Conf. in Low Temperature Physics
(1964) 394